



401 N. Raddant Rd.
 Batavia, IL 60510
 ph: 630-761-8900
 fx: 630-761-8989



Technical Data Sheet

Apollo 2000

Product Description

Apollo 2000 is a single component low viscosity cyanoacrylate adhesive. It is a fast setting wicking grade adhesive ideal for bonding preassembled parts.

Physical Properties

Monomer (Liquid)

Base Compound	Ethyl Cyanoacrylate
Appearance	Colorless Liquid
Viscosity (cP @ 68 °F)	3 cP
Specific Gravity (g/cc)	1.06
Flash Point (TCC)	185 °F
Shelf Life @40 °F	1 year unopened

Military Specifications

Mil-A-46050C
 Type II, Class 1

Curing Properties

Ambient surface moisture will initiate the hardening process. Handling strength is reached in a short period of time and varies depending on environmental conditions and substrates being bonded. Product will continue to cure for at least 24 hours before full strength and resistances are developed.

Setting Time (68 °F, 65% R.H.)

Steel	5 to 10 seconds
Aluminum	7 to 14 seconds
Neoprene	< 5 seconds
ABS	3 to 5 seconds
Polycarbonate	5 to 10 seconds
PVC	3 to 5 seconds

Curing Performance

The gap of the bond line will affect set speed. Smaller gaps tend to increase the speed. Activators can be applied to improve set speed but may also impair overall adhesive performance.

NOT FOR PRODUCT SPECIFICATIONS. THE DATA CONTAINED HEREIN ARE INTENDED AS REFERENCE ONLY. PLEASE CONTACT CYBERBOND L.L.C. TECHNICAL DEPARTMENT FOR ASSISTANCE AND RECOMMENDATIONS. CYBERBOND L.L.C. BATAVIA, IL 60510PHONE: 630-761-8900 FAX: 630-761-8989

IMPORTANT NOTICE: Cyberbond L.L.C. makes no warranties, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose. The specific user of this product is responsible for determining whether this Cyberbond product is fit for their particular purpose and suitable for user's method or application.

Polymer (Cured)

Appearance	Colorless Solid
Service Temperature Range	-65 °F to 200 °F
Softening Point	329 °F
Refractive Index (ND 20)	1.49
Full Cure Time	24 Hours
Dielectric Strength (KV/mm)	11.6
Dielectric Constant (@ 1Kc)	5.4
COE (in./in./F)	.000126
Tensile Strength (steel/steel)	3200 psi
Solubility	Nitromethane, Acetone, Dimethylformamide


Performance of Cured Materials

Tensile Shear strength after 48 hours at 20 ° to 25 °C

Substrate	Range in N/mm2
Blasted Steel	19 to 25
Etched Aluminum	12 to 20
Neoprene	> 10
ABS	> 6
Polycarbonate	> 5
PVC	> 6

Temperature Resistance

Sheer Strength on steel after 1 week at 22 °C





401 N. Raddant Rd.
 Batavia, IL 60510
 ph: 630-761-8900
 fx: 630-761-8989



Chemical Resistance

Sheer strength on steel after 12 month soak
 % Strength Retained

Solvent	% Strength Retained
Motor Oil	100
Gasoline	100
Trichloroethane	100
Freon TA	100
10% NaOH	0
10% Hcl	0
Water	0

General Instructions

Surfaces to be bonded should be clean and dry. Dispense a drop or drops to one surface only. Apply only enough to leave a thin film layer after compression.

Press parts together and hold firmly for a few seconds. Good contact is essential. An adequate bond develops in less than one minute and maximum strength is attained in 24 hours.

Wipe off excess adhesive from the top of the container and recap. Apollo products if left uncapped may deteriorate by contamination from moisture in the air.

Because Apollo products cure by polymerization, whitening may appear on the surface of the container or the bonded materials. Should this happen, wipe surfaces well with acetone.

Storage

Products should be stored unopened in a cool, dry place out of direct sunlight. Products can be refrigerated for improved shelf life but should be brought back to room temperature before use.

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS)

NOTE

The data contained herein are furnished for information only and are believed to be reliable. Cyberbond L.L.C. cannot assume responsibility for the results obtained by others over whose method Cyberbond L.L.C. does not control. It is the user's responsibility to determine suitability for the product or of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Cyberbond L.L.C. specifically disclaims all warranties of merchantability or fitness for a particular purpose arising from sale or use of Cyberbond L.L.C. products. Cyberbond L.L.C. specifically disclaims any liability for consequential or incidental damages of any kind, including loss of profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Cyberbond L.L.C. patents which may cover such processes or compositions. We recommend that each prospective user test the proposed application to determine its suitability for the purpose intended prior to incorporating any product or application in its manufacturing process using the data as a guide.

Curbell Plastics is a proud supplier of Cyberbond materials

Nationwide
1.888.CURBELL
www.curbellplastics.com