

# RAKU-TOOL® WB-0700

## Board Material

### Epoxy Board for Tools & Molds

PC - Rev.-Status: 01- 2006/01/24

Page 1 of 2

**Key Properties**

- Very fine surface structure
- Very easily machined
- Good dimensional stability
- Heat resistant up to 135°C

**Applications**

- Lay up tools for pre-preg
- Vacuum forming molds
- High temperature applications

**Mechanical Properties**

			<b>WB-0700</b>
Color	visual		Light green
Density	ASTM D-790	g/cm <sup>3</sup> (lb/ft <sup>3</sup> )	0.70 (43.8)
Shore hardness D	ASTM D-2240		70 – 80
Coefficient of thermal expansion	ASTM D-3386	10 <sup>-6</sup> K <sup>-1</sup> (in/in/°F x 10 <sup>-6</sup> )	35 – 45 (19 – 25)
Deflection temperature, HDT	ASTM D-648	°C (°F)	135 – 140 (275 – 284)
Compressive strength	ASTM D-695	MPa (psi)	50 – 55 (7,100 – 7,800)
Flexural strength	ASTM D-790	MPa (psi)	30 – 40 (4,200 – 5,700)

**Processing**

The product should have a temperature of 20°C – 25°C (68-77°F) during processing.

**Packaging**

RAKU-TOOL® WB-0700

1500 x 500 x 50 mm  
 (59.1 x 19.7 x 2.0 in)  
 1500 x 500 x 75 mm  
 (59.1 x 19.7 x 3.0 in)  
 1500 x 500 x 100 mm  
 (59.1 x 19.7 x 3.9 in)

**Storage**

The material should be stored flat and in a dry place. Temperature variations should be avoided during storage and transportation.

**RAKU-TOOL® WB-0700**  
Board Material  
Epoxy board for Tools and Molds

---

### Handling Precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.

---

**Curbell Plastics is a proud supplier  
of Rampf® materials**

**CURBELL**  
CURBELL PLASTICS, INC.

Nationwide  
**1.888.CURBELL**  
[www.curbellplastics.com](http://www.curbellplastics.com)

RAMPF Group, Inc.  
P.O. Box 930352  
50714 Century Ct.  
Wixom, MI 48393-2066  
T: (248) 295-0223  
F: (248) 295-0224  
E: [info@rampf-tooling.com](mailto:info@rampf-tooling.com)

[www.raku-tool.com](http://www.raku-tool.com)

Our recommendations on the use of the material are based on many years of experience and current scientific and practical knowledge. They are, however, provided without any obligation on our part and do not relieve the buyer of the need for suitability tests. They do not constitute a legal relationship, nor are any protected third party rights whatsoever affected thereby.