

PVC (polyvinyl chloride, rigid)



Rigid PVC is a strong, stiff, low cost plastic material that is easy to fabricate and easy to bond using adhesives or solvents. It is also easy to weld using thermoplastic welding equipment. PVC is frequently used in the construction of tanks, valves, and piping systems.

KEY CHARACTERISTICS:

- Strong and stiff
- Low cost
- Easy to weld using thermoplastic welding equipment
- Easy to join using solvents or adhesives
- FDA compliant grades available

APPLICATIONS:

- Welded tanks
- Manifolds
- Valve and pump housings
- Fittings
- Piping systems
- Cabinets and working surfaces

PVC TYPICAL PROPERTIES:

| | UNITS | ASTM TEST | PVC (RIGID) |
|---|-----------------------------|-----------|-------------|
| Tensile strength | psi | D-638 | 7,500 |
| Flexural modulus | psi | D-790 | 481,000 |
| Izod impact (notched) | ft-lbs/in of notch | D-256 | 1.0 |
| Heat deflection temperature @264 psi | °F | D-648 | 158 |
| Maximum continuous service temperature in air | °F | | 140 |
| Water absorption (immersion 24 hours) | % | D-570 | 0.06 |
| Coefficient of linear thermal expansion | in/in/°F x 10 ⁻⁵ | D-696 | 3.2 |

Standard Sizes: SHEET: 48"x96" (0.06"-3.0" thick) ROD: diameter 0.25"-12.0"

Length, width, thickness, and diameter tolerances vary by size and by manufacturer • Custom sizes and colors available upon request • Many of our materials are available as films with thicknesses of 0.029" or less. Values may vary according to brand name. Please ask your Curbell Plastics representative for more specific information about an individual brand.

Curbell Plastics has been supplying plastic sheet, rod, tube, films, adhesives, sealants, and prototyping materials for over 65 years



NATIONWIDE
1.888.CURBELL
www.curbellplastics.com

©2008 Curbell Plastics, Inc. All other trademarks and service marks are property of the respective manufacturers. All statements, technical information and recommendations contained in this publication are presented in good faith, based upon tests believed to be reliable and practical field experience. The reader is cautioned, however, that Curbell, Inc. cannot guarantee the accuracy or completeness of this information, and it is the customer's responsibility to determine the suitability of specific products in any given application.

PVCDataSheet 0308