

RAKU-TOOL® SB-0240

Board Material

Polyurethane Board for Styling & Design

PC - Rev.-Status: 01- 2006/01/24

Page 1 of 2

Key Properties

- Very good surface structure
- Easily machined
- Good heat resistance
- Resistant to organic solvents

Applications

- Styling models
- Epoxy laminating molds
- Support structures
- Negative molds for casting

Mechanical Properties

			SB-0240
Color	visual		Apricot
Density	ASTM D-790	g/cm ³ (lb/ft ³)	0.24 (15.0)
Coefficient of thermal expansion	ASTM D-3386	10 ⁻⁶ K ⁻¹ (in/in/°F x 10 ⁻⁶)	60 – 70 (33 – 39)
Deflection temperature, HDT	ASTM D-648	°C (°F)	55 – 65 (130 – 150)
Compressive strength	ASTM D-695	MPa (psi)	2 – 4 (290 – 570)
Flexural strength	ASTM D-790	MPa (psi)	5 – 6 (720 – 850)

Processing

The product should have a temperature of 20°C – 25°C (68-77°F) during processing.

Packaging

RAKU-TOOL® SB-0240	96 x 24 x 4 in 96 x 24 x 8 in 96 x 48 x 2 in 96 x 48 x 4 in
--------------------	--

Storage

The material should be stored flat and in a dry place. Temperature variations should be avoided during storage and transportation.

RAKU-TOOL® SB-0240

Board Material

Polyurethane Board for Styling & Design

Handling Precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.

**Curbell Plastics is a proud supplier
of Rampf® materials**

CURBELL
CURBELL PLASTICS, INC.

Nationwide
1.888.CURBELL
www.curbellplastics.com

RAMPF Group, Inc.
P.O. Box 930352
50714 Century Ct.
Wixom, MI 48393-2066
T: (248) 295-0223
F: (248) 295-0224
E: info@rampf-tooling.com

www.raku-tool.com

Our recommendations on the use of the material are based on many years of experience and current scientific and practical knowledge. They are, however, provided without any obligation on our part and do not relieve the buyer of the need for suitability tests. They do not constitute a legal relationship, nor are any protected third party rights whatsoever affected thereby.