

AMGARD polycarbonate sheet

AMGARD

AMGARD clear polycarbonate sheet is formulated with silver ion antimicrobial technology that protects the sheet surface from microorganism growth and remains active for the entire life of the product. When used as protective barriers, AMGARD polycarbonate sheet provides a clear solid partition between individuals. It is easy to fabricate and form for a wide range of interior applications.

- » Inhibits microbe surface degradation
- » Independent laboratory tested
- » Half the weight of glass
- » Does not shatter into sharp-edged pieces like glass
- » Easy to fabricate & clean

APPLICATIONS

Protective barriers, office partitions, safety enclosures, equipment housings

Typical Properties*

Property	Test Method	Units	Values
PHYSICAL			
Specific Gravity	ASTM D 792	-	1.2
Light Transmission, Clear @ 0.118"	ASTM D 1003	%	86
Water Absorption, 24 hours	ASTM D 570	%	0.15
MECHANICAL			
Tensile Strength, Ultimate	ASTM D 638	psi	9,500
Tensile Strength, Yield	ASTM D 638	psi	9,000
Tensile Modulus	ASTM D 638	psi	340,000
Elongation	ASTM D 638	%	110
Flexural Strength	ASTM D 790	psi	13,500
Flexural Modulus	ASTM D 790	psi	345,000
Instrumented Impact @ 0.125"	ASTM D 3763	ft-lbs	43
Rockwell Hardness	ASTM D 785	-	M70 / R118
THERMAL			
Coefficient of Thermal Expansion	ASTM D 696	in/in/°F	3.75 x 10 ⁻⁵
Coefficient of Thermal Conductivity	ASTM C 177	BTU-in/hr-ft ² -°F	1.35
Heat Deflection Temperature @ 264 psi	ASTM D 648	°F	270
Heat Deflection Temperature @ 66 psi	ASTM D 648	°F	280
FLAMMABILITY			
Horizontal Burn, AEB	ASTM D 635	in	<1
Ignition Temperature, Self	ASTM D 1929	°F	1000
Ignition Temperature, Flash	ASTM D 1929	°F	800

*Typical properties are not intended for specification purposes.

AMGARD polycarbonate sheet

CURBELL
PLASTICS

1-888-CURBELL

www.curbellplastics.com

Curbell Plastics is a proud supplier of Plaskolite materials.

These suggestions and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of use are beyond our control. We recommend that the prospective user determines the suitability of our materials and suggestions before adopting them on a commercial scale.

© 2020 **PLASKOLITE, LLC** 072020

TUFFAK® is a registered trademark of Plaskolite LLC

PLASKOLITE

400 Nationwide Blvd, Suite 400
Columbus, OH 43215
800.848.9124 • Fax: 877.538.0754
plaskolite@plaskolite.com
www.plaskolite.com

PDS200_AM POLY