

2965/2975

GLASS -SILICONE

Saint-Gobain Performance Plastics CHR® 2965-8R and 2975-8R are manufactured from silicone rubber/fiberglass cloth backing coated with high-temperature adhesive.

Typical Properties

Product Number	2965-8R	2975-8R
Backing Material	Glass-Silicone	Glass-Silicone
Adhesive Type	Silicone	Silicone
Total Thickness (in.)	.0105	.0105
Backing Thickness (in.)	.0070	.0070
Adhesion Thickness (in.)	.0035	.0035
Adhesion to Steel (oz/in.)	45	50
Tensile Strength (lbs./in.)	100	150
Dielectric Strength (volts)	4000	7000
Elongation (% at break)	15	5
Operating Temperature (°F)	-100 TO 500	-100 TO 500
Color	Blue	White

Values shown are typical. Certified test reports for writing specifications are available.

Applications—2965 and 2975 are used in the plasma spray process—a method of applying thin coatings of metal or high-temperature ceramics to a surface. The coating is sprayed at high pressure and at extreme temperatures. The tape is applied adjacent to areas of parts, which are to be plasma sprayed. These tapes protect these areas both from the grit blasting, which is used as a surface preparation, and from the actual plasma spray coating. The aerospace industry is the prime market for the use of plasma spray tapes, specifically, jet engine manufacturers, overhaul centers, major airline maintenance centers, Air Force Bases, and Naval Air Rework Facilities (NARF'S).

Features/Benefits—2965 and 2975 tapes are designed to withstand both the punishing abrasion of grit blasting and the extreme temperatures/pressures associated with the plasma spray process. The adhesive is a high-temperature silicone, which allows the product to withstand continuous temperatures up to 500°F and also prevents tape slippage after application. These tapes have excellent strength and flexibility, which allows for easy wrapping of complex shapes and minimizes wrinkling during the flexing of cables.

Availability—Factory stock for 2965 and 2975 is in master rolls 36 yards by 48". Rolls can be slit in widths ranging from 1/4 to 48". They are available with either a yellow PVC liner (2975-8RY) or a Fluorosilicone liner (2975-8RK).

CURBELL
PLASTICS

1-888-CURBELL

www.curbellplastics.com

Curbell Plastics is a proud supplier of Saint-Gobain Performance Plastics materials


SAINT-GOBAIN
PERFORMANCE PLASTICS

Typical Properties – Metric

Product Number	2965-8R	2975-8R
Backing Material	Glass-Silicone	Glass-Silicone
Adhesive Type	Silicone	Silicone
Total Thickness (mm.)	0.2667	0.2667
Backing Thickness (mm.)	0.1778	0.1778
Adhesion Thickness (mm.)	0.0889	0.0889
Adhesion to Steel (g/cm.)	502	558
Tensile Strength (kg./cm.)	17.8	26.8
Dielectric Strength (volts)	4000	7000
Elongation (% at break)	15	5
Operating Temperature (°C)	-73 to 260	-73 to 260
Color	Blue	White

Values shown are typical. Certified test reports for writing specifications are available.

For more information contact our customer service office or e-mail: norton-pi@saint-gobain.com



www.norton-films.com/norton-film-groups.aspx

Saint-Gobain Performance Plastics The Americas

14 McCaffrey Street
Hoosick Falls, NY 12090
Tel: (518) 686-7301
(800) 962-2666
Fax: (800) 526-8479

Saint-Gobain Performance Plastics Europe

Bay 3 Transpennine Industrial Estate
Gorrels Way
Rochdale OL 11 2PX
UK
Tel: +44 (0) 1706.746900
Fax: +44 (0) 1706.746991

Saint-Gobain Performance Plastics Asia

Room 302, 3F-1
147 Jianguo North Road, Section 2
Taipei, Taiwan, 104
Tel: (886) 2-2503-4201
Fax: (886) 2-2503-4202

NORTON®, StablEdge®, UL® and FluoroWrap™ are registered trademarks.

Limited Warranty: For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics Corporation warrants this product to be free from defects in materials and workmanship. Our only obligation will be to replace any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risk, if any, including the risk of injury, loss or damage, direct or consequential, arising out of the use, misuse, or inability to use, this product. THIS WARRANTY IS IN LIEU OF THE WARRANTIES OF MERCHANTABILITY, FITNESS FOR PARTICULAR PURPOSE, AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED. No deviation is authorized.



Note: Saint-Gobain Performance Plastics Corporation does not assume any responsibility or liability for any advice furnished by it, or for the performance or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and/or user. The purchaser and/or user should perform its own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.