



CHR[®] 2975-8R

Glass-Silicone Pressure Sensitive Adhesive Tape

CHR 2975-8R is manufactured from silicone rubber/fibreglass cloth backing coated with high-temperature adhesive.

Features/Benefits

2975 tape is designed to withstand both the punishing abrasion of grit blasting and the extreme temperatures/pressures associated with the plasma spray process. The adhesive is a high-temperature silicone, which allows the product to withstand continuous temperatures up to 260°C and also prevents tape slippage after application. These tapes have excellent strength and flexibility, which allows for easy wrapping of complex shapes and minimizes wrinkling during the flexing of cables.



Availability

Factory stock for 2975 is in master rolls 33 m × 1219 mm (36 yd × 48 in). Rolls can be slit in widths ranging from 6.35 mm to 1219 mm (0.25 in to 48 in). They are available with either a yellow PVC liner (2975-8RY) or a fluorosilicone liner (2975-8RK). Factory stock for 2975-8RK is in master rolls 33 m × 457 mm (36 yd × 18 in).

Applications

2975 is used in the plasma spray process: a method of applying thin coatings of metal or high-temperature ceramics to a surface. The coating is sprayed at high pressure and at extreme temperatures. The tape is applied adjacent to areas of parts, which are to be plasma sprayed. These tapes protect these areas both from the grit blasting, which is used as a surface preparation, and from the actual plasma spray coating. The aerospace industry is the prime market for the use of plasma spray tapes, specifically, jet engine manufacturers, overhaul centres, major airline maintenance centres, Air Force Bases, and Naval Air Rework Facilities (NARF'S).

CHR 2975-8R Properties

Performance tests are run using standard test procedures.

The values presented are typical values and should not be used for specification purposes.

Product Number	2975-8R
Backing Material	Glass-Silicone
Adhesive Type	Silicone
Total Thickness mm (mil)	0.267 (10.5)
Backing Thickness mm (mil)	0.178 (7.0)
Adhesive Thickness mm (mil)	0.089 (3.5)
Adhesion to Steel N/cm (oz/in)	5.5 (50)
Tensile Strength N/cm (lb/in)	263 (150)
Dielectric Strength (volts)	7,000
Elongation (% at break)	5
Operating Temperature °C (°F)	-73 to +260 (-100 to +500)
Colour	White



Saint-Gobain Tape Solutions

North America | South America | Europe | Asia

For a full list of locations, please visit
tapesolutions.saint-gobain.com/contact-us

CURBELL
PLASTICS

1-888-CURBELL

www.curbellplastics.com

Curbell Plastics is a proud supplier of Saint-Gobain Tape Solutions

IMPORTANT: It is the user's responsibility to ensure the suitability and safety of Saint-Gobain products for all intended uses and that the materials to be used comply with all applicable regulatory requirements. Saint-Gobain assumes no responsibility for any product failures that occur due to misuse of the materials it provides arising out of the design, fabrication or application of the products into which the materials are incorporated.

WARRANTY: For a period of 6 months, Saint-Gobain warrants this product(s) to be free from defects in manufacturing. The only obligation under any applicable product warranty will be to replace any portion proving defective, or at our option, to refund the purchase price thereof. SAINT-GOBAIN DISCLAIMS ALL IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

Form #1133 | © Saint-Gobain July 2020 | **CHR** and **CHRTape** are trademarks of Saint-Gobain.