

## Foamlite® P

### Product characteristics

- Low density
- Nearly no moisture absorption
- High tensile strength

### Typical field of application

- Industry packing systems
- Reusable containers
- Insulating lining

	Test method	Unit	Value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g/cm <sup>3</sup>	0,65
Water absorption	DIN EN ISO 62	%	<0,1
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
<b>Mechanical properties</b>			
Yield stress	DIN EN ISO 527	N/mm <sup>2</sup>	18
Elongation at break	DIN EN ISO 527	%	>50
Tensile modulus of elasticity	DIN EN ISO 527	MPa	1100
Impact strength	DIN EN ISO 527	%	24
Shore hardness	DIN EN ISO 868	scale D	70
<b>Thermal properties</b>			
Melting temperature	ISO 11357-3	°C	162-167
Thermal conductivity	DIN 52612-1	W / (m * K)	0,10 – 0,15
Thermal capacity	DIN 52612	kJ / (kg * K)	1,70
Coefficient of linear thermal expansion	DIN 53752	10 <sup>-6</sup> K <sup>-1</sup>	120-190
Service temperature, long term	Average	°C	-10 ... 90
Service temperature, short term (max.)	Average	°C	150
Heat deflection temperature	DIN EN ISO 306, Vicat B	°C	149
<b>Electrical properties</b>			
Dielectric constant	IEC 60250		2,3
Dielectric dissipation factor (10 <sup>6</sup> Hz)	IEC 60250		0,00019
Volume resistivity	IEC 60093	Ω *cm	>10 <sup>14</sup>
Surface resistivity	IEC 60093	Ω	>10 <sup>13</sup>
Comparative tracking index	IEC 60112		600
Dielectric strength	IEC 60243	kV/mm	40

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

Röchling Engineering Plastics SE & Co. KG  
 Röchlingstr. 1 · D-49733 Haren/Germany · Tel. +49 5934 701-0 · Fax +49 5934 701-299 · info@roechling-plastics.com · www.roechling.com