

HYDEX® 4101 UD Blue (TECADUR PBT UD blue) - Stock Shapes (rods, plates, tubes)

Chemical Designation

PBT (Polybutylene terephthalate)

Colour

blue

Density

1.59 g/cm³

Fillers

detectable filler

Main features

- resistant to cleaning agents
- food grade blue
- good chemical resistance
- good dimensional stability
- good impact strength
- metal detectable
- x-ray opaque

Target Industries

- food technology
- food processing
- food engineering
- conveyor technology
- packaging and paper machinery

Mechanical properties	condition	value		test method	comment
Tensile strength	@ 73 °F	9,300	psi	ASTM D 638	
Modulus of elasticity (tensile test)	@ 73 °F	550,000	psi	ASTM D 638	
Elongation at break (tensile test)	@ 73 °F	3.53	%	ASTM D 638	
Flexural strength	@ 73 °F	15,250	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	556,150	psi	ASTM D 790	
Compression strength	@ 73 °F, 10% strain	13,760	psi	ASTM D 695	
Compression strength	@ 73 °F, 1% strain	3,200	psi	ASTM D 695	
Compression modulus	@ 73 °F	346,360	psi	ASTM D 695	
Impact strength (Izod)	Notched	0.58	ft-lbs/in	ASTM D 256	
Rockwell hardness	M-Scale	92		ASTM D 785	
Thermal properties	condition	value		test method	comment
Melting temperature		437	°F	-	(1) Injection molded samples
Deflection temperature	@ 66 psi	393	°F	ASTM D 648	(2) Injection molded samples
Deflection temperature	@ 264 °F	275	°F	ASTM D 648	(3) Per UL 746B
Service temperature	Long Term	221	°F	-	(4) Injection molded samples
Thermal expansion (CLTE)		4.05	*10 ⁻⁵ in/in/°F	ASTM D 696	
Other properties	condition	value		test method	comment
Moisture absorption	@24 hr, 73 °F	0.2	%	ASTM D 570	

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.

Ensinger Inc. Headquarters
365 Meadowlands Boulevard
Washington, PA 15301, USA

Phone 800-243-3221 Sales
Phone 800-869-4029 Technical
Fax 724-746-9209
sales@ensingerusa.com

Date: 2017/03/07

Version: A1



Curbell Plastics is a proud supplier of Ensinger materials.