

KYDEX® Thermoplastic Sheet

High impact, thermoplastic sheet that is tough, durable, and easy to form



KYDEX® Thermoplastic Sheet is an excellent choice for applications where appearance, toughness, or complex thermoforming is required. It is used for thermoformed equipment housings, airplane, bus and train interior parts, kiosks, medical devices, and POP displays.

KYDEX® Thermoplastic Sheet Material Options

Bonding KYDEX® Thermoplastics – Use Plexus® MA300, a fast-setting methacrylate adhesive, to create stronger bonds than the KYDEX® Sheet itself.

KYDEX® 100 – Rigid, tough, durable, plastic alloy sheet available in a wide range of standard and custom colors, textures, and sheet sizes. It is Underwriters Laboratories® Inc. recognized for UL Std 94 V-0, 5V and has 961 J/m (18 ft-lbs/in) Notched Izod impact resistance.

KYDEX® T – High impact fire-rated sheet that is less hygroscopic and usually does not require pre-drying. Offers more uniform forming with less wall thinning. Greater resistance to a broad range of corrosive chemicals and cleaning solutions.

KYDEX® T Sheet for O&P – Used by fabricators in the orthotics industry for neck braces, body jackets and upper extremity orthoses. KYDEX® Sheet provides rigidity, excellent formability, and mar-resistance.

KYDEX® Thermoplastic Sheet is widely used for:

- Kiosks, exhibits, and display bases
- Counters, workstations, and kickplates
- Furniture components, shelving, and cabinetry
- Medical device and closures
- Flat laminated panels of all types
- Thermoformed equipment housings
- Aviation and mass transit interiors
- Membrane pressed components

Performance characteristics:

- Easy to thermoform deep-draw parts
- Maintains excellent part definition and crisp detail
- High impact resistance to breakage
- Good strength and stiffness
- Easy machining and fabricating using conventional methods and equipment
- Consistent color throughout the KYDEX® material helps hide scratches and wear

Available in:



Sheet

TYPICAL PROPERTIES OF KYDEX® THERMOPLASTIC SHEET

	UNITS	ASTM TEST	KYDEX® 100	KYDEX® T
Tensile strength	psi	D638	6,100	6,100
Flexural modulus	psi	D790	335,000	360,000
Izod impact (notched)	ft-lbs/in of notch	D256	18.0	15.0
Heat deflection temperature @ 264 psi	°F	D648	173	168
Maximum continuous service temperature in air	°F		-	-
Water absorption (immersion 24 hours)	%	D570	0.05-0.08	0.08
Coefficient of linear thermal expansion	in/in/°Fx10 ⁻⁵	D696	4.2	3.8

Values may vary according to brand name. Please ask your Curbell Plastics representative for more specific information about an individual brand.