

NOVAMID® AM1030 FR (F)

Technical data	Dry	Unit	Test Method
Tensile modulus	3500 / -	MPa	ISO 527-1/-2
Yield stress	57 / -	MPa	ISO 527-1/-2
Yield strain	2,8 / -	%	ISO 527-1/-2
Stress at break	50 / -	MPa	ISO 527-1/-2
Strain at break	7 / -	%	ISO 527-1/-2
Charpy impact strength (+23°C)	29,7 / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	3 / -	kJ/m ²	ISO 179/1eA

**For more information and buying options,
please visit www.dsm.com/additive-manufacturing/**

DSM – Bright Science. Brighter Living.™

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of aforementioned information, or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequences from the use of all such information. Novamid® is a trademark of DSM.

Copyright © DSM 2019. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of DSM. Doc 0025-01

CURBELL
PLASTICS

