

OPTIX DA acrylic sheet

OPTIX DA (Digital Acrylic) sheet is specifically designed to provide optimal adhesion of UV curing inks without adhesion promoters. OPTIX DA delivers all the benefits of continuously processed acrylic sheet in a specially formulated product for printing. It can be used in interior and exterior applications.

Just as with OPTIX sheet, OPTIX DA provides superior strength and is available in a variety of gauges 0.060" - 0.236" with standard and run-to-size options. Call Customer Service for details.

APPLICATIONS

Signage, graphics and dry-erase boards

Typical Properties*			
Property	Test Method	Units	Values
PHYSICAL			
Specific Gravity/Relative Density	ASTM D792	-	1.19
Light Transmission - Total	ASTM D1003	%	>86
Water Absorption	ASTM D570	%	0.4
MECHANICAL			
Tensile Strength	ASTM D638	psi	11,030
Tensile Modulus of Elasticity	ASTM D638	psi	490,000
Flexural Strength	ASTM D790	psi	17,000
Izod Impact Strength - Notched	ASTM D256	ft-lb/in	0.4
THERMAL			
Maximum Recommended Continuous Service Temperature	-	°F	170-190
Deflection Temperature @ 264 psi (1.8 MPa)	ASTM D648	°F	203
Coefficient of Thermal Expansion	ASTM D696	in/in/°F	3.0x10 ⁻⁵

*Typical properties are not intended for specification purposes

OPTIX DA acrylic sheet

CURBELL
PLASTICS

1-888-CURBELL

www.curbellplastics.com

Curbell Plastics is a proud supplier of Plaskolite materials.

These suggestions and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of use are beyond our control. We recommend that the prospective user determines the suitability of our materials and suggestions before adopting them on a commercial scale.

© 2021 **PLASKOLITE, LLC** 042021

OPTIX® is a registered trademark of Plaskolite LLC

PLASKOLITE

400 Nationwide Blvd, Suite 400
Columbus, OH 43215
800.848.9124 • Fax: 877.538.0754
plaskolite@plaskolite.com
www.plaskolite.com

PDS233