

# tonerplastics

## PETG 3D Filament Data Sheet

### Polyethylene Terephthalate - Glycol Modified (PETG)

PETG is a durable and strong thermoplastic which combines many desirable features from other plastics into one material. PETG offers similar mechanical properties to that of ABS while maintaining the ease of use of PLA. PETG has low thermal shrinkage in comparison to other materials making it a great choice for objects in which high levels dimensional accuracy is required.

Mechanical Properties	
Intrinsic Viscosity, dL/g	0.80 ± 0.02
Glass Transition Temp, C	80
Specific Density, g/cm <sup>3</sup>	> 1.29
Size Specifications	
Nominal Outer Diameter, mm	1.75/2.88
OD Tolerance, mm	±0.05
Ovality, mm	< 0.05

### Applications

- General purpose 3D printing
- Heavy use prints
- Engineering and industrial prototyping

### Recommended Printer Settings

- Extruder Temperature: 230-250 °C
- Bed Temperature: 80-100 °C
- Printing Speed: 50-80 mm/s
- Bed Adhesion: Hair Spray or Painters Tape

### Additional Information

- Sizes Available: 1.75/2.88mm (Custom Sizes Available)
- Spool Weight: 1 kg (2.2 lbs.) (Custom Sizes Available)
- Custom packaging methods available upon request
- All filaments are sealed with desiccants

### Regulatory Compliance

- RoHS
- REACH
- California Proposition 65

#### Disclaimer:

The above information is provided in good faith. Toner Plastics assumes no obligation or liability for the accuracy or completeness of the information supplied in this document. It is solely the customers responsibility to determine if the product and information in this document are appropriate for the customers end use. Responsibility for the use, storage, handling, and disposal of the products herein is that of the purchaser or end user.

**CURBELL**  
PLASTICS

1-888-CURBELL

[www.curbellplastics.com](http://www.curbellplastics.com)