

## SUSTAPEEK

	ASTM Test method	Unit	Value
<b>Physical Properties</b>			
Specific Gravity	D792	g/cm <sup>3</sup>	1.32
Water Absorption 24 hours	D570	%	0.1
Water Absorption Saturation	D570	%	0.5
Dissipation Factor	D150	1 MHz	0.003
<b>Mechanical Properties</b>			
Hardness	D785	Shore D	D85
Rockwell Hardness	D785	M	M105
Rockwell Hardness	D785	R	R126
Tensile Strength at yield 73 °F	D638	psi	16,000
Tensile Modulus	D638	psi	500,000
Elongation at Break	D638	%	20
Flexural Strength	D790	psi	25,000
Flexural Modulus	D790	psi	600,000
Compressive Strength	D695	psi	18,000
Shear Strength	D732	psi	7,700
Izod Impact, Notched	D256	ft-lb/in	1.2
Coefficient of Friction, Dynamic	-	-	0.4
<b>Thermal properties</b>			
CTE, linear	D696	in/in/°F	2.6x10 <sup>-5</sup>
Melting Point	D3418	°F	630
Continuous Use	-	°F	480
Thermal Conductivity	-	in/hr/ft <sup>2</sup> /F°	1.73
Deflection Temperature at 1.8Mpa (66psi)	D648	°F	360
Deflection Temperature at 1.8Mpa (264psi)	D648	°F	320
Flammability, UL94	-	1/8 inch	V-0
<b>Electrical properties</b>			
Dielectric constant	D150	-	3.3
Surface resistivity	D257	Ohm/cm	10 <sup>15</sup>
Dielectric strength	D149	V/mil	480
<b>Compliance Properties</b>			
FDA	-	-	Yes

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

Röchling Engineering Plastics  
903 Gastonia Technology Parkway, Dallas, NC 28034, USA - Tel.: 704 922 7814 - info@roechling-plastics.us - www.roechling-plastics.us

Status: April 19, 2016



Curbell Plastics is a proud supplier of Röchling materials.

