

# SentryGlas®

IONOPLAST INTERLAYER

## SPECIFYING AND TECHNICAL DATA

The following information is presented to help you evaluate or order SentryGlas® ionoplast interlayers. SentryGlas® interlayer is available on roll or as sheet and has a Yellowness-Index (ZID) of < 2.5.

### SHEET DIMENSIONS

Caliper (mm) (mil)	Width (cm) (in) Ordered, -0 +7 mm (-0 +¼ in)	Length (cm) (in)
0.89 (35)	61-216 (24-85)	up to 600 (up to 236)
1,52 (60)	61-216 (24-85)	up to 600 (up to 236)
2,28 (90)	61-216 (24-85)	up to 600 (up to 236)
2,53 (100)	61-183 (24-72)	up to 600 (up to 236)
3,04 (120)	61-183 (24-72)	up to 600 (up to 236)

In addition to the standard stock sizes above, SentryGlas® can be ordered as 'cut-to-size', 'cut-to-fit' or 'cut-to-form' sheet, which means that none of the material is wasted. In all cases, sheet thickness is 0.89 mm (35 mil), 1.52 mm (60 mil) or 2.28 mm (90 mil). As these custom sizes require special handling/cutting, lead times are longer.

### ROLL DIMENSIONS

Caliper (mm) (mil)	Width (cm) (in) Ordered, -0 +7 mm (-0 +¼ in)	Length (m) (feet)
0.89 (35)	122 (48), 153 (60), 183 (72)	200 (656)
0.89 (35)	153 (60)	50 (164)

For details about the 'cut-to-size', 'cut-to-fit' or 'cut-to-form' sheet offering feel free to contact us.

## SentryGlas® Elastic Properties (SG5000)

TABLE 1 – LAMINATE PROPERTIES

Property	Units Metric (English)	Value	Test
Haze	%	< 2	ASTM D1003
Impact test 2.27 kg (5 lb)	m (ft)	> 9.14 (> 30)	ANSI Z26.1
Boil test 2 hr	-	No defects	ANSI Z26.1
Bake test 2 hr/100 °C	-	No defects	ANSI Z26.1

TABLE 2 – INTERLAYER TYPICAL PROPERTIES

Property	Units Metric (English)	Value	ASTM Test
Young's Modulus	Mpa (kpsi)	300 (43.5)	D5026
Tear Strength	MJ/m3 (ft lb/in3)	50 (604)	D638
Tensile Strength	Mpa (kpsi)	34.5 (5.0)	D638
Elongation	% (%)	400 (400)	D638
Density	g/cm3 (lb/in3)	0.95 (0.0343)	D792
Flex Modulus 23 °C (73 °F)	Mpa (kpsi)	345 (50)	D790
Heat Deflection Temperature (HDT)@0.46 MPa	°C (°F)	43 (110)	D648
Melting Point	°C (°F)	94 (201)	(DSC)
Coeff. of Thermal Expansion (-20 °C to 32 °C)	10-3 cm/cm °C (mils/in °C)	10 - 15 (0.10 - 0.15)	D696
Thermal Conductivity	W/M-K (BTU-in/hr-ft2 °F)	0.246 (1.71)	

# SentryGlas® Elastic Properties (SG5000)

## YOUNG'S MODULUS: SENTRYGLAS®

Young's Modulus E MPa (psi)		Load Duration						
		1 s	3 s	1 min	1 h	1 day	1 mo	10 yrs
Temperature	10 °C (50 °F)	692. (1.00 E+05)	681. (98745)	651. (94395)	597. (86565)	553. (80185)	499. (72355)	448. (64960)
	20 °C (68 °F)	628. (91060)	612. (88740)	567. (82215)	493. (71485)	428. (62060)	330. (47850)	256. (37120)
	24 °C (75 °F)	581. (84245)	561. (81345)	505. (73225)	416. (60320)	327. (47415)	217. (31465)	129. (18705)
	30 °C (86 °F)	442. (64090)	413. (59885)	324. (46980)	178. (25810)	148. (21460)	34.7 (5032)	15.9 (2306)
	40 °C (104 °F)	228. (33060)	187. (27115)	91.6 (13282)	27.8 (4031)	13.6 (1972)	9.86 (1430)	8.84 (1282)
	50 °C (122 °F)	108. (15660)	78.8 (11426)	33.8 (84901)	12.6 (1827)	8.45 (1225)	6.54 (948.3)	6.00 (870)
	60 °C (140 °F)	35.3 (5119)	24.5 (3553)	10.9 (1581)	5.10 (739.5)	3.87 (561.2)	3.24 (469.8)	2.91 (422)
	70 °C (158 °F)	11.3 (1639)	8.78 (1273)	5.64 (817.8)	2.52 (365.4)	1.77 (256.7)	1.44 (208.8)	1.35 (195.8)
	80 °C (176 °F)	4.65 (674.3)	3.96 (574.2)	2.49 (361.1)	0.96 (139.2)	0.75 (108.8)	0.63 (91.4)	0.54 (78.3)

## SHEAR MODULUS: SENTRYGLAS®

Shear Modulus G MPa (psi)		Load Duration						
		1 s	3 s	1 min	1 h	1 day	1 mo	10 yrs
Temperature	10 °C (50 °F)	240. (34800)	236. (34220)	225. (32625)	206. (29870)	190. (27550)	171. (24795)	153. (22185)
	20 °C (68 °F)	217. (31465)	211. (30595)	195. (28275)	169. (24505)	146. (21170)	112. (16240)	86.6 (12557)
	24 °C (75 °F)	200. (29000)	193. (27985)	173. (25085)	142. (20590)	111. (16095)	73.2 (10614)	43.3 (6279)
	30 °C (86 °F)	151. (21895)	141. (20445)	110. (15950)	59.9 (8686)	49.7 (7207)	11.6 (1682)	5.31 (770)
	40 °C (104 °F)	77.0 (11165)	63.0 (9135)	30.7 (4452)	9.28 (1346)	4.54 (658.3)	3.29 (477.1)	2.95 (427.8)
	50 °C (122 °F)	36.2 (5249)	26.4 (3828)	11.3 (1639)	4.20 (609)	2.82 (408.9)	2.18 (316.1)	2.00 (290)
	60 °C (140 °F)	11.8 (1711)	8.18 (1186)	3.64 (527.6)	1.70 (246.5)	1.29 (187.1)	1.08 (156.6)	0.97 (140.7)
	70 °C (158 °F)	3.77 (546.7)	2.93 (424.9)	1.88 (272.6)	0.84 (121.8)	0.59 (85.6)	0.48 (69.6)	0.45 (69.6)
	80 °C (176 °F)	1.55 (224.8)	1.32 (191.4)	0.83 (120.4)	0.32 (46.4)	0.25 (36.3)	0.21 (30.5)	0.18 (26.1)

# SentryGlas® Elastic Properties (SG5000)

## POISSON RATIO: SENTRYGLAS®

Poisson Ratio, $\nu$		Load Duration						
		1 s	3 s	1 min	1 h	1 day	1 mo	10 yrs
Temperature	10 °C (50 °F)	0.442	0.443	0.446	0.450	0.454	0.458	0.463
	20 °C (68 °F)	0.448	0.449	0.446	0.459	0.464	0.473	0.479
	24 °C (75.2 °F)	0.452	0.453	0.458	0.465	0.473	0.482	0.489
	30 °C (86 °F)	0.463	0.466	0.473	0.485	0.488	0.497	0.499
	40 °C (104 °F)	0.481	0.484	0.492	0.498	0.499	0.499	0.499
	50 °C (122 °F)	0.491	0.493	0.497	0.499	0.499	0.500	0.500
	60 °C (140 °F)	0.497	0.498	0.499	0.500	0.500	0.500	0.500
	70 °C (158 °F)	0.499	0.499	0.500	0.500	0.500	0.500	0.500
	80 °C (176 °F)	0.500	0.500	0.500	0.500	0.500	0.500	0.500

## POLYMER INTERLAYER BEHAVIOR

### All interlayers are viscoelastic

- Stiffness (modulus) and Poisson ratio vary as a function of temperature and load duration (creep)
- Evaluate properties over a range of test temperature and time using dynamic mechanical analysis and creep tests (ASTM D 4065)
- 'Small' strain values (< 20% engineering strain)

### Young's Modulus, E, shear modulus, G & Poisson ratio, U.

- Extract E, G and U for specified temperature and load duration
- Choose appropriate elastic property values for design case and assign to an effective elastic interlayer
- Important to assess the likelihood of achieving full design load at the design temperature and load duration

Copyright © 2014 Kuraray. All rights reserved. SentryGlas® is a registered trademark of E. I. du Pont de Nemours and Company or its affiliates for its brand of interlayers. It is used under license by Kuraray. The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Kuraray cannot anticipate all variations in actual end-use conditions, Kuraray make no warranties and assume no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under a recommendation to infringe any patent rights. Document Ref. GLS-TECUBU-2014-11