

Product Data

Somos[®] ProtoCast 19122

Description

DSM's Somos[®] ProtoCast 19122 is a breakthrough for the investment casting industry. It is an antimony-free liquid photopolymer specifically formulated for producing investment casting patterns.

Applications

Ideal for use in foundry applications, Somos[®] ProtoCast 19122 is totally antimony-free, which eliminates the risk of contamination in specialty alloys. Antimony is traditionally present in the photoinitiators that activate the stereolithography chemistry. No other metals are present in this unique photopolymer chemistry.

The absence of antimony also allows stereolithography patterns to burn out more completely, resulting in significantly lower residual ash than is produced by burning out conventional stereolithography patterns. Studies have shown that the residual ash of Somos[®] ProtoCast 19122 is less than 0.015% after burnout at 1500°F for two hours.

TECHNICAL DATA - LIQUID PROPERTIES

Appearance	Clear Peach
Viscosity	~100 cps @ 30°C
Density	~1.13 g/cm ³ @ 25°C

TECHNICAL DATA - OPTICAL PROPERTIES

E _c	11.5 mJ/cm ²	[critical exposure]
D _p	5.20 mils	[slope of cure-depth vs. ln (E) curve]
E ₁₀	85 mJ/cm ²	[exposure that gives 0.254 mm (.010 inch) thickness]

TECHNICAL DATA			
Mechanical Properties		Somos® ProtoCast 19122 UV Postcure	
ASTM Method	Property Description	Metric	Imperial
D638M	Tensile Modulus	2,013 - 2,187 MPa	292.0 - 317.2 ksi
D638M	Tensile Strength at Break	44.5 - 45.3 MPa	6.5 - 6.6 ksi
D638M	Elongation at Break	6%	6%
D790M	Flexural Strength	73 - 76 MPa	10.6 - 11.0 ksi
D2240	Flexural Modulus	2,135 - 2,265 MPa	309.7 - 328.5 ksi
D2240	Hardness (Shore D)	84 - 86	84 - 86
D256A	Izod Impact (Notched)	0.17 - 0.29 J/cm	0.32 - 0.54 ft-lb/in
D570-98	Water Absorption	0.70%	0.70%

TECHNICAL DATA			
Thermal/Electrical Properties		Somos® ProtoCast 19122 UV Postcure	
ASTM Method	Property Description	Metric	Imperial
E831-05	C.T.E. -40 - 0°C (-40 - 32°F)	74.1 µm/m°C	41.2 µin/in°F
E831-05	C.T.E. 0 - 50°C (32 - 122°F)	96.3 µm/m°C	53.5 µin/in°F
E831-05	C.T.E. 50 - 100°C (122 - 212°F)	141.8 µm/m°C	78.8 µin/in°F
E831-05	C.T.E. 100 - 150°C (212 - 302°F)	182.0 µm/m°C	101.1 µin/in°F
D150-98	Dielectric Constant 60 Hz	3.16	3.16
D150-98	Dielectric Constant 1 KHz	3.12	3.12
D150-98	Dielectric Constant 1 MHz	2.94	2.94
D149-97A	Dielectric Strength	14.53 - 15.24 kV/mm	369 - 387 V/mil
E1545-00	Tg	49°C	120°F
D648	HDT @ 0.46 MPa (66 psi)	59°C	138°F
D648	HDT @ 1.81 MPa (264 psi)	50°C	122°F




Curbell Plastics is a proud supplier of DSM Somos® materials.

DSM Functional Materials Somos® Materials Group

in North America

1122 St. Charles Street
Elgin, Illinois 60120
USA
Phone: +1.847.697.0400

in Europe

Slachthuisweg 30
3150 XN Hoek van Holland
The Netherlands
Phone: +31.174.315.391

in China

476 Li Bing Road
Zhangjiang Hi-Tech Park
Pudong New Area
Shanghai 201203, China
Phone: +86.21.6141.8064

Visit us online at www.dsm.com/somos

NOTICE : Somos® is a registered trademark of Royal DSM N.V. Somos® is an unincorporated subsidiary of DSM Desotech Inc. The information presented herein is based on generally accepted analytical and testing practices and is believed to be accurate. However, DSM Desotech expressly disclaims any product warranties which may be implied including warranties or merchantability and/or fitness for a particular purpose DSM Desotech's products are sold subject to DSM Desotech's standard terms and conditions of sale, copies of which are available upon request. Purchasers are responsible for determining the suitability of the product for its intended use and the appropriate manner of utilizing the product in purchaser's production processes and applications so as to insure safety, quality and effectiveness. Purchasers are further responsible for obtaining necessary patent rights to practice any invention in connection with the use of purchased product and any other product or process. DSM Desotech reserves the right to change specifications of their products without notice. © 2012 DSM IP ASSESTS B.V. All rights reserved.