



Product Data Sheet

Somos[®] WaterShed 11110

Description

DSM's Somos[®] WaterShed 11110 is a low viscosity liquid photopolymer that produces strong, tough, water-resistant, ABS-like parts. Most importantly, parts created with Somos[®] WaterShed 11110 are nearly colorless, and look more like true, clear engineered plastic.

In addition, Somos[®] WaterShed has been formulated with the DSM's Somos[®] Oxetane Advantage™ — an advanced chemistry platform that produces parts with outstanding water resistance and high dimensional stability.

Applications

Somos[®] WaterShed 11110 offers many properties that mimic traditional engineering plastics, including ABS and PBT. This makes the material ideal for many applications in the automotive, medical and consumer electronic markets and include lenses, packaging, water flow analysis, RTV patterns, durable concept models, wind tunnel testing and quickcast patterns.

TECHNICAL DATA - LIQUID PROPERTIES

Appearance	Optically clear, near colorless
Viscosity	~92 cps @ 30°C
Density	~1.12 g/cm ³ @ 25°C

TECHNICAL DATA - OPTICAL PROPERTIES

E _c	~11.5 mJ/cm ²	[critical exposure]
D _p	5.45 mils	[slope of cure-depth vs. ln (E) curve]
E ₁₀	72 mJ/cm ²	[exposure that gives 0.254 mm (.010 inch) thickness]

TECHNICAL DATA							
Mechanical Properties		Somos® WaterShed 11110 UV Postcure		ABS (Transparent)		Polybutylene Terephthalate	
ASTM Method	Property Description	Metric	Imperial	Metric	Imperial	Metric	Imperial
D638M	Tensile Strength at Break	48.3 MPa	7.1 ksi	45.7 MPa	6.6 ksi	55 MPa	8.1 ksi
D638M	Elongation at Break	25%	25%	41.6%	41.6%	20%	20%
D638M	Elongation at Yield	3.4%	3.4%	N/A	N/A	3.5 - 9%	3.5 - 9%
D638M	Modulus of Elasticity	2,640 MPa	383 ksi	2,000 MPa	290 ksi	2,700 MPa	392 ksi
D790M	Flexural Strength	63.7 MPa	9.2 ksi	73.5 MPa	10.7 ksi	80 MPa	11.6 ksi
D790M	Flexural Modulus	2,140 MPa	310 ksi	2,300 MPa	344 ksi	2,500 MPa	363 ksi
D256A	Izod Impact (Notched)	0.19 J/m	0.36 ft-lb/in	1.6 J/m	1.5 - 2.0 ft-lb/in	1.2 J/m	0.56 ft-lb/in
D542	Index of Refraction	N/A	N/A	1.52	1.52	N/A	N/A
D2240	Hardness (Shore D)	N/A	N/A	N/A	N/A	98 - 120	98 - 120
D1004-09	Graves Tear	132,746 N/m	758 ft-lb/in	N/A	N/A	N/A	N/A
D570-98	Water Absorption	0.35%	0.35%	0.20 - 0.45%	0.20 - 0.45%	0.16%	0.16%

TECHNICAL DATA							
Thermal/Electrical Properties		Somos® WaterShed 11110 UV Postcure		ABS (Transparent)		Polybutylene Terephthalate	
ASTM Method	Property Description	Metric	Imperial	Metric	Imperial	Metric	Imperial
E831-05	C.T.E. -40 - 0°C (-40 - 32°F)	68.6 µm/m°C	38 µin/in°F	60 - 130 µm/m°C	33 - 72 µin/in°F	50 - 145 µm/m°C	28 - 81 µin/in°F
E831-05	C.T.E. 0 - 50°C (32 - 122°F)	103.9 µm/m°C	58 µin/in°F				
E831-05	C.T.E. 50 - 100°C (122 - 212°F)	186.8 µm/m°C	104 µin/in°F				
E831-05	C.T.E. 100 - 150°C (212 - 302°F)	176.6 µm/m°C	98 µin/in°F				
D150-98	Dielectric Constant 60 Hz	3.5	3.5	3.7	3.7	2.9 - 4.0	2.9 - 4.0
D150-98	Dielectric Constant 1 KHz	3.5	3.5	N/A	N/A	2.9 - 4.0	2.9 - 4.0
D150-98	Dielectric Constant 1 MHz	3.2	3.2	3.7	3.7	2.9 - 4.0	2.9 - 4.0
D149-97A	Dielectric Strength	2,995 kV/mm	17.1 V/mil	13.8 - 19.7 kV/mm	350 - 500 V/mil	14.7 - 30 kV/mm	373 - 762 V/mil
E1545-00	Tg	41°C	106°F	N/A	N/A	41°C	106°F
D648	HDT @ 0.46 MPa (66 psi)	49.6°C	121°F	94 - 207°C	201 - 405°F	150°C	302°F
D648	HDT @ 1.81 MPa (264 psi)	46.2°C	115°F	86.4 - 194°C	187 - 381°F	61.3°C	142.3°F



Curbell Plastics is a proud supplier of DSM Somos® materials.

**DSM Functional Materials
Somos® Materials Group**

in North America

1122 St. Charles Street
Elgin, Illinois 60120
USA
Phone: +1.847.697.0400

in Europe

Slachthuisweg 30
3150 XN Hoek van Holland
The Netherlands
Phone: +31.174.315.391

in China

476 Li Bing Road
Zhangjiang Hi-Tech Park
Pudong New Area
Shanghai 201203, China
Phone: +86.21.6141.8064

Visit us online at www.dsm.com/somos

NOTICE: Somos® is a registered trademark of Royal DSM N.V. Somos® is an unincorporated subsidiary of DSM Desotech Inc. The information presented herein is based on generally accepted analytical and testing practices and is believed to be accurate. However, DSM Desotech expressly disclaims any product warranties which may be implied including warranties of merchantability and/or fitness for a particular purpose. DSM Desotech's products are sold subject to DSM Desotech's standard terms and conditions of sale, copies of which are available upon request. Purchasers are responsible for determining the suitability of the product for its intended use and the appropriate manner of utilizing the product in purchaser's production processes and applications so as to insure safety, quality and effectiveness. Purchasers are further responsible for obtaining necessary patent rights to practice any invention in connection with the use of purchased product and any other product or process. DSM Desotech reserves the right to change specifications of their products without notice.
© 2012 DSM IP ASSESTS B.V. All rights reserved.