

TECAFORM® AH ID blue - Stock Shapes

Chemical Designation

POM-C (Polyacetal (Copolymer))

Colour

blue

Density

1.48 g/cm³

Fillers

detectable filler

Main features

- metal detectable
- easy to machine
- excellent mechanical properties
- good wear properties
- low moisture absorption
- good dimensional stability

Target Industries

- food processing
- conveyor technology
- engineering for beverage filling systems
- pharmaceutical industry
- packaging and paper machinery

<i>Mechanical properties</i>	<i>condition</i>	<i>value</i>		<i>test method</i>	<i>comment</i>
Modulus of elasticity (tensile test)	@ 73 °F	450,000	psi	ASTM D 638	
Tensile strength at yield	@ 73 °F	9,500	psi	ASTM D 638	
Elongation at break	@ 73 °F	10	%	ASTM D 638	
Flexural strength	@ 73 °F	15,000	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	450,000	psi	ASTM D 790	
Compression strength	@ 73 °F, 10% strain	14,000	psi	ASTM D 695	
Compression strength	@ 73 °F, 1% strain	3,100	psi	ASTM D 695	
Compression modulus		300,000	psi	ASTM D 695	
Impact strength (Izod)	@ 73 °F	0.77	ft-lbs/in	ASTM D 256	
Rockwell hardness	M Scale	91		ASTM D 785	
<i>Thermal properties</i>	<i>condition</i>	<i>value</i>		<i>test method</i>	<i>comment</i>
Melting temperature		329	°F	ASTM D 2133	(1) publicly sourced data
Service temperature	Intermittent	285	°F	-	1)
Service temperature	Long Term	212	°F	-	2)
Thermal expansion (CLTE)		7.7*10 ⁻⁵	in/in/°F	ASTM D 696	3)
<i>Electrical properties</i>	<i>condition</i>	<i>value</i>		<i>test method</i>	<i>comment</i>
Specific surface resistance		1.0*10 ¹²	Ω/square	-	
<i>Other properties</i>	<i>condition</i>	<i>value</i>		<i>test method</i>	<i>comment</i>
Moisture absorption	@ saturation, 73 °F	0.65	%	ASTM D 570	
Moisture absorption	@ 24 hrs, 73 °F	0.22	%	ASTM D 570	

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.

Ensinger Inc. Headquarters
365 Meadowlands Boulevard
Washington, PA 15301, USA

Phone 800-243-3221 Sales
Phone 800-869-4029 Technical
Fax 724-746-9209
sales@ensinger-ind.com

Date: 2017/08/10

Version: A0

CURBELL
PLASTICS

1-888-CURBELL

www.curbellplastics.com

Curbell Plastics is a proud supplier of Ensinger materials.