

TECAPEEK SM GF30 natural

Chemical designation

PEEK (polyetheretherketone)

Colour

Beige opaque

Density

1.53 g/cm³

Fillers

Glass fibres

Main features

- electrically insulating
- high thermal and mechanical capacity
- hydrolysis and superheated steam resistant
- good chemical resistance
- flame retardant according to UL94 V-0
- high dimensional stability
- good slide and wear properties
- very high stiffness
- very high creep resistance

Target Industries

- oil and gas Industry
- chemical technology
- mechanical engineering
- electrical engineering
- aircraft and aerospace technology
- automotive industry
- conveyor technology
- vacuum technology
- textile industry

Mechanical properties	parameter	value	unit	norm	comment
Modulus of elasticity (tensile test)		7230	MPa	BS EN ISO 527-2	
Tensile strength		107	MPa	BS EN ISO 527-2	
Tensile strength at yield		107	MPa	BS EN ISO 527-2	
Elongation at yield		2.1	%	BS EN ISO 527-2	
Elongation at break		2.1	%	BS EN ISO 527-2	
Flexural strength		165	MPa		
Modulus of elasticity (flexural test)		6380	MPa		
Shore D hardness		89		BS EN ISO 868	

Thermal properties	parameter	value	unit	norm	comment
Glass transition temperature		147	°C	DIN 53765	1)
Melting temperature		341	°C		2)
Service temperature	short term	300	°C		2)
Service temperature	long term	260	°C		2)

(1) Found in public sources.
 (2) Found in public sources.
 Individual testing regarding application conditions is mandatory.



Curbell Plastics is a proud supplier of Ensinger materials.

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes.