# tonerplastics

#### **ABS 3D Filament Data Sheet**

# **Acrylonitrile Butadiene Styrene** (ABS)

ABS is a high strength, flexible thermoplastic suitable for printing objects which may be used in high temperature or industrial settings. Due to its high glass transition temperature, a heated bed is required to successfully print with ABS. For the best results when printing with ABS, a fully enclosed print bed is recommended.

Mechanical Properties		Test Method
Tensile Strength @ Break, PSI	5800	ASTM D638
Yield Strength, PSI	6520	ASTM D638
Tensile Elongation, %	2.6	ASTM D638
Notched Izod Impact, ft-lb/in	1.12	ASTM D256
Size Specifications		
Nominal Outer Diameter, mm	1.75/2.88	-
OD Tolerance, mm	±0.05	-
Ovality, mm	< 0.05	-

# **Applications**

- General purpose 3D printing
- Heavy use prints
- Objects which will be exposed to high temperatures

### **Recommended Printer Settings**

Extruder Temperature: 220-240 °C

Printing Speed: 50-90 mm/s

Bed Temperature: 100-130 °C

Bed Adhesion: Hair Spray or ABS Glue

#### **Additional Information**

- Sizes Available: 1.75/2.88mm (Custom Sizes Available) Spool Weight: 1 kg (2.2 lbs.) (Custom Sizes Available)
- Custom packaging methods available upon request
- All filaments are sealed with desiccants

## **Regulatory Compliance**

**RoHS** 

**REACH** 

#### **Disclaimer:**

The above information is provided in good faith. Toner Plastics assumes no obligation or liability for the accuracy or completeness of the information supplied in this document. It is solely the customers responsibility to determine if the product and information in this document are appropriate for the customers end use. Responsibility for the use, storage, handling, and disposal of the products herein is that of the purchaser or end user.

