

CORZAN® CPVC

TYPICAL PHYSICAL PROPERTIES	UNITS OF MEASURE	VALUE	ASTM METHOD
Physical			
Density	g/cm ³	1.47	D 792
Water Absorption	%	.03	D 570
Rockwell Hardness	R Scale	117	D 2842
Hardness	Shore D	85	D 2240
Cell Class	-	23446	D 1784
Mechanical			
Izod Impact	ft-lb/in	10.0	D 256
Tensile Strength	psi	7,300	D 638
Tensile Modulus	psi	390,000	D 638
Flexural Strength	psi	12,700	D 790
Flexural Modulus	psi	382,000	D 790
Compressive Modulus	Psi	156,300	D 695
Thermal			
Heat Deflection Temp (264 psi)	°F	194	D 648
Coefficient of Linear Expansion	in/in/°F	3.9 x 10 ⁻⁵	D 696
Thermal Conductivity	BTU	0.95	C 177
Flammability Ratings			
Vertical Burn Test	-	V-0	UL 94 (tested, not listed)
Limiting Oxygen Index	%	58 - 62	D 2863
Fire Resistance (per NSF standards)	in/min	Did not burn	D635
Electrical			
Dielectric Strength	kV/cm	1,250	D 147
Dielectric Constant	60 HZ	3.70	D 150
Volume Resistivity	Ohm / cm	3.4 x 10 ¹⁵	D 257
Power Factor	100 HZ	0.01%	D 150

Physical properties of plastic sheeting are represented as 'Typical'. Information contained herein is considered accurate to the best of our knowledge. It is offered for your consideration and investigation, and is not to be construed as representation or warranty expressed or implied. Our warranties are limited to those expressly stated in formal contracts or in conditions of sale on our invoices and order acceptances. Conditions and methods of use may vary and are beyond the control of Vycom Corporation; therefore, Vycom Corporation disclaims any liability incurred as a result of the use of this product in accordance with the data contained in our physical property charts. No information herein shall be construed as an offer of indemnity for infringement or as a recommendation to use the products in such a manner as to infringe any patent, domestic or foreign.

The 'Typical' properties of our plastic sheet cannot be automatically used when engineering finished components, and the fabricator or end user is responsible for insuring the suitability of our products for their specific application or end use!