

Bayfol[®] UV506 7-2 030002

Characterization

Bayfol UV506 7-2 030002 is an enhanced extrusion lamination film based on Makrolon[®] polycarbonate.

Properties / Applications

Bayfol UV506 7-2 030002 is virtually glare-free and has excellent scratch resistance. This product has been developed especially for critical graphic applications to provide UV resistance. Typical applications are gas pump graphics, harsh exterior environments, nameplates and labels.

Bayfol UV506 7-2 030002 is available in a standard thickness of 0.030 inch (750 microns). Other thicknesses are available on request. The surface combination of Bayfol UV506 7-2 030002 is one side velvet and one side very fine matte. As with any product, use of Bayfol UV506 7-2 030002 in a given application must be tested (including, but not limited to, field testing) in advance by the user to determine suitability.

Typical Properties*

Property	Test Method	Value, U.S. Units	Value, S.I. Units
General			
Specific Gravity	ASTM D 792	1.21	1,21
Conversion Factor		159 ft ² /lb•mil	0.826 m ² /kg•mm
Gloss 60° top side, black inked second surface	ASTM D 2457	4 to 9 gloss unit	4 to 9 gloss unit
Surface		velvet/v.f. matte	
Mechanical			
Tensile Strength, Yield	ASTM D 882	8,500 psi	58,6 MPa
Elongation at Break	ASTM D 882	100 %	100 %
Tear Strength, Initiation	ASTM D 1004	1,200 lb#in	210 kN/m
UV Resistance			
Xenon Arc. 3000 hr.	SAE J2527 C2	< 2 ΔYI	< 2 ΔYI
Xenon Arc. 3000 hr.	SAE J2527 C2	< 1.0 ΔE	< 1,0 ΔE
Optical			
Light Transmittance	ASTM D 1003	> 70 % (> 30 mil)	> 70 % (> 760 micron)
Yellowness Index	ASTM E 313	1	1

* These items are provided as general information only. They are approximate values and are not part of the product specifications.



Bayfol[®] UV506 7-2 030002

Other Information

Bayfol[®] is a registered trademark of Covestro AG.

Makrolon[®] is a registered trademark of Covestro AG.

Health and Safety Information

Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling this product. Before working with this product, you must read and become familiar with the available information on its risks, proper use, and handling. This cannot be overemphasized. Information is available in several forms, e.g., safety data sheets and product labels. For further information contact your Covestro LLC representative or the Product Safety and Regulatory Affairs Department in Pittsburgh, PA.

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

Editor: Covestro LLC
1 Covestro Circle
Pittsburgh, Pennsylvania 15205
United States
www.covestro.com

Contact:
8 Fairview Way South Deerfield, MA 01373
Tel. 413-665-7016

page 2 of 2

Document contains important information and must be read in its entirety.

Edition 2022-01-26

 **Bayfol[®]**

Product Datasheet