

DuPont™ Vespel® SP-1

POLYIMIDE ISOSTATIC SHAPES

Typical ISO Properties

DuPont™ Vespel® SP-1 parts and shapes are specified for their excellent physical properties, including electrical and thermal insulation at high temperatures. SP-1 is an unfilled polymer.

Some data presented below are based on limited production runs and are subject to revision as new knowledge and experience become available.

Mechanical Property	Temperature	ASTM	Units	Typical Values
Tensile Strength	23 °C (73 °F) 260 °C (500 °F)	D-1708 or E8†	MPa (ksi)	86.2 (12.5) 41.4 (6.0)
Strain at Break	23 °C (73 °F) 260 °C (500 °F)	D-1708 or E8†	%	7.5 6.0
Flexural Strength	23 °C (73 °F) 260 °C (500 °F)	D-790	MPa (kpsi)	110.3 (16.0) 62.1 (9)
Flexural Modulus	23 °C (73 °F) 260 °C (500 °F)	D-790	MPa (kpsi)	3102 (450) 1724 (250)
Compressive Stress				
at 1% strain	23 °C (73 °F)	D-695	MPa (kpsi)	24.8 (3.6)
at 10% strain	23 °C (73 °F)			133.1 (19.3)
at 0.1% offset	23 °C (73 °F)			51.0 (7.4)
Compressive Modulus	23 °C (73 °F)	D-695	MPa (kpsi)	2413 (350)
Axial Fatigue, Endurance Limit				
at 10 ³ cycles	23 °C (73 °F) 260 °C (500 °F)	—	MPa (kpsi)	55.8 (8.10) 26.2 (3.8)
at 10 ⁷ cycles	23 °C (73 °F) 260 °C (500 °F)			42.1 (6.1) 16.5 (2.4)
Flexural Fatigue, Endurance Limit				
at 10 ³ cycles	23 °C (73 °F)	—	MPa (kpsi)	65.5 (9.5)
at 10 ⁷ cycles	23 °C (73 °F)			44.8 (6.5)
Shear Strength	23 °C (73 °F)	D-732	MPa (kpsi)	89.6 (13.0)
Izod Notched Impact Strength	23 °C (73 °F)	D-256	J/m	42.7
Izod Unnotched Impact Strength	23 °C (73 °F)	D-256	J/m	747
Poisson's Ratio	23 °C (73 °F)	—	—	0.41

Wear and Friction				
Wear Rate ^{††}	—	—	m/s x 10 ⁻¹⁰	17-85
Friction Coefficient ^{**} PV = 0.875 MPa· m/s PV = 3.5 MPa· m/s	—	—	—	0.29
In Vacuum	—	—	—	—
Static in Air	—	—	—	0.35
Thermal Property	Temperature	ASTM	Units	Typical Values
Coefficient of Linear Expansion	23 °C (73 °F) to 260 °C (500 °F) -62 to +23 (-80 to 73° F)	D-696	µm/m/°C (µin/in/°F)	54 (30) 45 (25)
Thermal Conductivity	40 °C (104 °F)	—	W/m· °C	0.35
Specific Heat	—	—	J/kg/°C	1130
Deformation Under 14 MPa Load	50 °C (122 °F)	D-621	%	0.14
Deflection Temperature at 2 MPa	—	D-648	°C	~360
Electrical Property				
Dielectric Constant at 10 ² Hz at 10 ⁴ Hz at 10 ⁶ Hz	23 °C (73 °F)	D150	—	3.62 3.64 3.55
Dissipation Factor at 10 ² Hz at 10 ⁴ Hz at 10 ⁶ Hz	23 °C (73 °F)	D150	—	0.0018 0.0036 0.0034
Dielectric Strength, Short Time 2 mm Thick	23 °C (73 °F)	D149	MV/m	22 (3.20)
Volume Resistivity	23 °C (73 °F)	D257	Ω· m	10 ¹⁴ –10 ¹⁵
Surface Resistivity	23 °C (73 °F)	D257	Ω	10 ¹⁵ –10 ¹⁶
Other Properties				
Water Absorption 24 h 48 h Equilibrium, 50% RH	23 °C (73 °F) 50 °C (122 °F)	D570	%	0.24 0.72 1.0–1.3
Specific Gravity	—	D792	—	1.43
Oxygen Index	—	D2863	%	53

† Machined isoststic tensile specimens made per D1708

† † Unlubricated in air (PV 0.875 MPa· m/s).

** Steady state, unlubricated in air.

Visit us at vespel.com

CURBELL
PLASTICS

1-888-CURBELL

www.curbellplastics.com

Curbell Plastics is a proud supplier of DuPont™ materials.

DUPONT
Authorized Distributor

The information set forth herein is furnished free of charge, is based on technical data that DuPont believes to be reliable and represents typical values that fall within the normal range of properties. This information relates only to the specific material designated and may not be valid for such material used in combination with other materials or in other processes. It is intended for use by persons having technical skill, at their own discretion and risk and it is not intended as a substitute for any testing you may conduct to determine for yourself the suitability of our products and information for your particular purpose. This information should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their conditions of use present no health or safety hazards and comply with applicable law. Since conditions of product use and disposal are outside our control, DUPONT DE NEMOURS, INC. AND ITS AFFILIATES MAKE NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AND ASSUMES NO LIABILITY IN CONNECTION WITH ANY USE OF THIS PRODUCT AND INFORMATION. As with any product, evaluation under end use with applicable law, conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

CAUTION: Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with the DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. DuPont's sole warranty is that our products will meet our standard sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DUPONT DE NEMOURS, INC. AND ITS AFFILIATES SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, MERCHANTABILITY, OR NON INFRINGEMENT. DUPONT DE NEMOURS, INC. AND ITS AFFILIATES DISCLAIMS LIABILITY FOR ANY SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.
© 2026 DuPont. All rights reserved.

Reference No. A20 VPE-A40172-00-B0526



dupont.com