

DuPont™ Vespel® Polyimide SP Family

Extremely high temperature creep resistant plastic
with excellent friction and wear characteristics



DuPont™ Vespel® Polyimide is an extremely high temperature, creep resistant plastic material that is often used in high heat environments where thermoplastic materials lose their mechanical properties. Vespel®, a lightweight alternative to metal, is available in a variety of formulations including unfilled grades and several low friction and wear grades.

DuPont™ Vespel® Polyimide Material Options

The Vespel® SP Family of products are highly durable polyimides used in demanding applications where exceptional thermal resistance, low wear and/or low friction, strength and impact resistance are desired.

SP-1 – Unfilled offers superior wear and insulation properties with operating temperatures from cryogenic to 260°C (500°F). Low electrical conductivity. Highest elongation and purity of SP family. Available as stock shapes.

SP-21 – Graphite-enhanced with low-friction properties for use with or without lubrication in various applications. Available as custom parts or stock shapes.

SP-211 – Lower coefficient of friction than SP-21 without lubrication in various applications. Available as custom parts or stock shapes.

SP-202 – Conductive, eliminates static charge in high temperature substrate handling applications.

SP-22 – Minimal thermal expansion and dimensional stability for design flexibility. Available as custom parts or stock shapes.

SP-3 – Used in vacuum and dry environments with low outgassing. Available as stock shapes.


DuPont™ Vespel® is widely used for:

- Semiconductor and material handling machinery
- Chip test sockets
- Wafer clamping rings
- Valve seats and sealing applications
- Spline couplings
- High performance bearings and bushings
- Locking fasteners for aerospace
- Pivot bushings on unison ring

Performance characteristics:

- Long term performance at temperatures up to 260°C (500°F)
- Outstanding sealing characteristics when mated against metals
- Excellent unlubricated bearing and wear properties (bearing grades)
- Good electrical insulating properties (unfilled grades)

Available in:



Sheet

Rod

AUTHORIZED DISTRIBUTOR

DuPont™ Vespel® DU PONT
PARTS & SHAPES

Supplying Authentic Vespel® Shapes

©2020 Curbell Plastics, Inc. Unauthorized use is strictly prohibited. All other trademarks, service marks and logos used herein are property of their respective owners. All rights hereto are retained by Curbell Plastics and any third party owners of such rights. All statements, technical information and recommendations contained in this publication are for informational purposes only. Curbell Plastics, Inc. does not guarantee the accuracy or completeness of any information contained herein and it is the customer's responsibility to conduct its own review and make its own determination regarding the suitability of specific products for any given application. MAP01557B 0320

CURBELL
PLASTICS

[CLICK, GET A QUOTE »](#)

www.curbellplastics.com • 1.888.CURBELL (287-2355)

TYPICAL PROPERTIES OF DUPONT™ VESPEL® POLYIMIDE SP

	ASTM Method	Units	SP-1 Unfilled	SP-21 15% Graphite	SP-22 40% Graphite	SP-211 15% Graphite and 10% Teflon®	SP-3 15% Vacuum Bearing Grade
Mechanical							
Tensile strength, 23°C (73°F)	D1708 /D638	MPa (kpsi)	86.2 (12.5)	65.5 (9.5)	51.7 (7.5)	44.8 (6.5)	56.5 (8.2)
Tensile strength, 260°C (500°F)	D1708 /D638	MPa (kpsi)	41.4 (6.0)	37.9 (5.5)	23.4 (3.4)	24.1 (3.5)	
Elongation at break, 23°C (73°F)	D1708 /D638	%	7.5	4.5	3.0	3.5	4.0
Elongation at break, 260°C (500°F)	D1708 /D638	%	6.0	3.0	2.0	3.0	
Flexural modulus, 23°C (73°F)	D790	MPa (kpsi)	3,100 (450)	3,790 (550)	4,830 (700)	3,100 (450)	3,280 (475)
Flexural modulus, 260°C (500°F)	D790	MPa (kpsi)	1,720 (250)	2,550 (370)	2,760 (400)	1,380 (200)	1,860 (270)
Compressive stress at 10% strain, 23°C (73°F)	D695	MPa (kpsi)	133 (19.3)	133 (19.3)	112 (16.3)	102 (14.8)	128 (18.5)
Deformation under 13.8 MPa (2,000 psi) load	D621	%	0.14	0.10	0.08	0.13	0.12
Friction							
Coefficient of friction at PV = .875 MPa m/s (25,000 psi-ft/min)*			0.29	0.24	0.20	0.12	0.25
Coefficient of friction at PV = 3.5 MPa m/s (25,000 psi-ft/min)*				0.12	0.09	0.08	0.17
Static coefficient of friction in air*			0.35	0.30	0.27	0.20	
PV limit (unlubricated)**		MPa-m/s (kpsi ft/min)		12.3 (350)	12.3 (350)	3.5 (100)	
Other Properties							
Coefficient of thermal expansion 23-300°C (73-572°F)	E831	µm/m/K (10 ⁻⁶ in/in-°F)	54 (30)	49 (27)	38 (21)	54 (30)	52 (29)
Hardness	D785	Rockwell E	45–60	25–45	5–25	1–20	40–55
Water absorption, 24 hr at 23°C (73°F)	D570	%	0.24	0.19	0.14	0.21	0.23

*Versus carbon steel, steady state, unlubricated, in air, thrust bearing. **PV limits for any material vary with different combinations of pressure and velocity as well as other conditions.

View Typical Properties for Vespel® SP-202 Conductive Grade at curbellplastics.com/research-solutions/DuPont-Vespel-SP-202.

The information set forth herein is furnished free of charge, is based on technical data that DuPont believes to be reliable, and represents typical values that fall within the normal range of properties. This information relates only to the specific material designated and may not be valid for such material used in combination with other materials or in other processes. It is intended for use by persons having technical skill, at their own discretion and risk. This information should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards and comply with applicable law. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

CAUTION: Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with the DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative.

DuPont's sole warranty is that our products will meet our standard sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DUPONT SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, MERCHANTABILITY, OR NON-INFRINGEMENT. DUPONT DISCLAIMS LIABILITY FOR ANY SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, ™ or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.

© 2020 DuPont. All rights reserved.

www.curbellplastics.com • 1.888.CURBELL (287-2355)