

KYDEX® 5555

Low heat release aviation sheet

Introduction

KYDEX® 5555 is specifically formulated to meet the safety needs of the aviation industry.

General Information

KYDEX® 5555 is a proprietary, high performance acrylic/PVC thermoplastic sheet that meets all fire retardancy requirements set forth in Federal Aviation Regulations 25.853 paragraphs (a) and (d) (old (c)) including low heat release (65/65) in the OSU rate of heat release test. KYDEX® 5555 exceeds the heat release to a level of 55/55. Its excellent properties make it the ideal material to form two-and-three-dimensional aircraft components.

Suggested Applications

- Seat parts
- Bulkhead laminates
- Life vest shrouds
- Passenger service units
- Monitor shrouds
- Armrests
- Moulding strips
- Tray tables
- Kick panels

Features

- Available in over 200 developed colours, various surface textures, and eight thicknesses ranging from 0.71mm and up.
- Very resistant to a wide range of concentrate chemicals, and is therefore easy to clean with aggressive cleaners such as Soft Scrub®, Fantastic®, and citrus-based cleaners such as Citri Kleen®. Ammoniated cleaners should be avoided since they can leave a residue.
- Meets the stringent requirements of the FAR 25.853 paragraph (d) (replaces para.c), in all thicknesses and colours.

SEKISUI SPI

Customer Service

6685 Low St, Bloomsburg, PA 17815 USA
Phone: 800.325.3133, +1.570.389.5810
Outside the US: +1.570.389.5814
Fax: 800.452.0155, +1.570.387.7786
Email: info@sekisui-spi.com

Technical Service

Phone: 800.682.8758
Fax: +1.570.387.8722
Outside the US: +1.570.387.6997
techservice@sekisui-spi.com

sekisui-spi.com

CURBELL
PLASTICS

1-888-CURBELL

www.curbellplastics.com

Curbell Plastics is a proud supplier of SEKISUI SPI materials

KYDEX® 5555

Low heat release aviation sheet

Environmental and Safety Considerations

Physical Properties

SEKISUI SPI is committed to ensuring that its products can be manufactured, transported, stored, used, disposed and recycled with an appropriate regard for safety, health and environmental protection. We support the safe handling of our products. Please contact our Technical Service department at 800.682.8758 for resources or visit our website: <http://www.sekisui-spi.com>. For Material Safety Data Sheets, please call 800.325.3133.

Property	Test Method	Typical Value ¹	
PHYSICAL			
Specific Gravity	ASTM D-792	1.52	
Rockwell Hardness, R-Scale	ASTM D-785	111	
MECHANICAL			
Tensile Strength	ASTM D-638	43 MPa	6,180 psi
Flexural Strength	ASTM D-790	81.2 MPa	11,780 psi
Modulus of Elasticity	ASTM D-790	3,833 MPa	556,000 psi
THERMAL			
Heat Deflection Temperature (HDT) @ 264 psi (1.8 MPa) annealed	ASTM D-648	75.9°C	168.6°F
FLAMABILITY²			
Vertical Burn, 60-second	FAR 25.853(a)(i)	Pass	
Vertical Burn, 12-second	FAR 25.853(a)(ii)	Pass	
Flammability: OSU Heat Release	FAR 25.853 (d) Part IV	Total: <55 kw/m ² Total: <55 kw/m ²	
Flammability: NBS Smoke Density	FAR 25.853(d) Part V	D max <150	
Forming Temperature		170-200°C	338-392°F
¹ Values based upon 3.18mm (0.125") sheet unless otherwise specified. ² All thicknesses 0.71mm (0.028") and above Not intended for specification purposes.			

This information is based upon standard laboratory tests and is provided for comparative purposes to substantiate antimicrobial activity for non-public health applications. Microban technology is not designed to protect users from disease causing microorganisms. Microban protection inhibits the growth of microorganisms that cause stains,

SEKISUI SPI

Customer Service

6685 Low St, Bloomsburg, PA 17815 USA
 Phone: 800.325.3133, +1.570.389.5810
 Outside the US: +1.570.389.5814
 Fax: 800.452.0155, +1.570.387.7786
 Email: info@sekisui-spi.com

Technical Service

Phone: 800.682.8758
 Fax: +1.570.387.8722
 Outside the US: +1.570.387.6997
techservice@sekisui-spi.com

[sekisui-spi.com](http://www.sekisui-spi.com)

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. THE PRODUCTS DISCUSSED ARE SOLD WITHOUT WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE, EITHER EXPRESSED OR IMPLIED, EXCEPT AS PROVIDED IN OUR STANDARD TERMS AND CONDITIONS OF SALE. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our product. Product not intended for use as a heat resistant surface. Texture, product grade and other conditions may cause variations in appearance.

This information supersedes all previously published data.