

OPTIX® L CONTINUOUS CAST ACRYLIC

OPTIX L continuous cast acrylic sheet has the highest clarity. It is easy to fabricate and form for many applications for interior and exterior applications with exceptional UV stability. It has superior thickness tolerance compared to cell cast sheets. OPTIX L is easy to clean and offers superior craze and chemical resistance. It is available in gauge range of 2.0mm - 8.0mm. Custom gauged and sheet sizes are available.

APPLICATIONS

Furniture, cosmetic displays, interior partitions, signage

TYPICAL METRIC PROPERTIES*

Property	Test Method	Units	Values
PHYSICAL			
Specific Gravity	ASTM D792	-	1.19
Optical Refractive Index	ASTM D542	-	1.49
Light Transmission- total	ASTM D1003	%	92
Light Transmission- haze	ASTM D1003	%	<1
Water Absorption	ASTM D570	%	0.2
MECHANICAL			
Tensile Strength	ASTM D638	MPa	76
Tensile Modulus of Elasticity	ASTM D638	MPa	3200
Flexural Strength	ASTM D790	MPa	101
Flexural Modulus of Elasticity	ASTM D790	MPa	3180
Izod Impact Strength - Milled Notch	ASTM D256	J/cm	0.17
Compressive Strength	ASTM D 695	MPa	574
Shear Strength	ASTM D732	MPa	77
Rockwell hardness	ASTM D785	-	M-100
THERMAL			
Maximum Recommended Continuous Service Temperature	-	°C	79
Deflection Temperature @ 1.8 MPa	ASTM D648	°C	93
Coefficient of Linear Thermal Expansion	ASTM D696	cm/cm/°C	6.3 x 10 ⁻⁵
Flammability (Burning Rate)	ASTM D635	cm/min	30
Flammability	UL 94	-	HB
Smoke Density Rating	ASTM D2843	%	13.5
Self-Ignition Temperature	ASTM D1929	°C	399
Flame Spread Index	ASTM E84	-	110
Smoke Developed Index	ASTM E84	-	530
ELECTRICAL			
Dielectric Constant @ 1 KHz	ASTM D150	-	3.0
Dielectric Constant @ 1 MHz	ASTM D150	-	2.7
Dielectric Strength	ASTM D149	V/mm	13900
Volume Resistivity	ASTM D257	Ohms/cm	>3.91 x 10 ¹⁵

These suggestions and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of use are beyond our control. We recommend that the prospective user determines the suitability of our materials and suggestions before adopting them on a commercial scale.

© 2023 PLASKOLITE, LLC 82023
OPTIX® is a registered trademark of Plaskolite LLC

PLASKOLITE

400 W Nationwide Blvd, Suite 400
Columbus, OH 43215
800.848.9124 • Fax: 877.538.0754
plaskolite@plaskolite.com
www.plaskolite.com



PDS304_OPX_L_Metric