

## FLAMETEC CLEANROOM PVC-C (FM 4910 LISTED PVC MATERIAL)

TYPICAL PHYSICAL PROPERTIES	UNITS OF MEASURE	VALUE	ASTM METHOD
<b>Physical</b>			
Density	g/cm <sup>3</sup>	1.53	D 792
Water Absorption	%	0.03	D 570
Hardness	Shore D	76	D 2240
Cell Class	-	23445	D 1784
<b>Mechanical</b>			
Tensile Strength @ Yield	psi	7,190	D 638
Tensile Modulus	psi	366,000	D 638
Notched Izod Impact	ft-lb/in	3.0	D 256
<b>Thermal</b>			
Heat Deflection Temp (66 psi)	°F	190	D 648
Heat Deflection Temp (264 psi)	°F	173	D 648
Coefficient of Linear Expansion	in/in/°F	3.3 x 10 <sup>-5</sup>	D 696
<b>Flammability</b>			
FM Global (Factory Mutual)	FM-4910 <sup>D+</sup>	Listed	-
Vertical Burn Test	UL-94*	V-0; 5-VA	-

\*: Meets UL 94 Testing Criteria

<sup>D</sup> Meets FM-4910 testing Criteria (1/4"-1" Only)

+ FM Listed

**CURBELL**  
PLASTICS

1-888-CURBELL

[www.curbellplastics.com](http://www.curbellplastics.com)

Curbell Plastics is a proud supplier of Plaskolite materials.

Physical properties of plastic sheeting are represented as 'Typical'. Information contained herein is considered accurate to the best of our knowledge. It is offered for your consideration and investigation, and is not to be construed as representation or warranty expressed or implied. Our warranties are limited to those expressly stated in formal contracts or in conditions of sale on our invoices and order acceptances. Conditions and methods of use may vary and are beyond the control of Vycom Corporation; therefore, Vycom Corporation disclaims any liability incurred as a result of the use of this product in accordance with the data contained in our physical property charts. No information herein shall be construed as an offer of indemnity for infringement or as a recommendation to use the products in such a manner as to infringe any patent, domestic or foreign.

The 'Typical' properties of our plastic sheet cannot be automatically used when engineering finished components, and the fabricator or end user is responsible for insuring the suitability of our products for their specific application or end use!

These suggestions and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of use are beyond our control. We recommend that the prospective user determines the suitability of our materials and suggestions before adopting them on a commercial scale.

FLAMETEC® is a registered trademarks of PLASKOLITE LLC

## PLASKOLITE

400 W Nationwide Blvd, Suite 400  
Columbus, OH 43215  
800.848.9124 • Fax: 877.538.0754  
[plaskolite@plaskolite.com](mailto:plaskolite@plaskolite.com)  
[www.plaskolite.com](http://www.plaskolite.com)

PDS502\_VYC\_Flametec\_PVC-C