



Metallic Gray Rapid Tooling Urethane

DESCRIPTION

REPLICAST 612 is a two-component, filled urethane tooling material that has very easy handling characteristics and exceptional cured properties. This material tends to have less hard-pack settling in storage, and therefore is usually easier to use than other materials of this type, which tend to settle more rapidly. It is not extremely abrasive, so it can be machined with the proper cutters if desired. REPLICAST 612 has a one-to-one mix ratio by weight or volume, for fast measuring and mixing. It has a longer pot life than earlier materials of this type, yet is cures rapidly, and can be demolded and put into service quickly. REPLICAST 612 has lower exotherm during cure than our REPLICAST 609, and therefore lower shrinkage in thicker castings. REPLICAST 612 is the better choice for thicker castings when the lowest shrinkage is required.

REPLICAST 612 provides an easy to measure and mix, rapid curing system that has tough cured properties and very good heat resistance. It is an excellent choice for patterns, tooling, fixtures and general shop aids.

FEATURES and BENEFITS

- Less Hard-Pack Filler Settling
- Smooth Consistency that Pours Well & Duplicates Details Nicely
- ♦ Low Exotherm During Cure for **Stress-Free Castings**
- Very Good Hot Strength
- ◆ Excellent for Medium to Larger Casts ◆ Low Shrinkage, Good Cured Stability

PRODUCT SPECIFICATIONS

		REPLICAST 612 Part A	REPLICAST 612 Part B	Test Method
Color		Gray	Tan	Visual
Viscosity, @ 77 ^o F, centipoise		2,700 cps	500 cps	ASTM D23932
Specific Gravity, gms./cc		1.73	1.69	ASTM D1475
Mix Ratio	By Weight By Volume	100 : 100 100 : 100		PTM&W
Pot Life, 4 fl. Oz. Mass, @ 77°F		10 minutes		ASTM D2471

Page 1

Inasmuch as PTM&W Industries, Inc. has no control over the use to which others may put material, it does not guarantee that the same results as those described herein will be obtained. The above data was obtained under laboratory conditions, and to the best of our knowledge is accurate. This information is presented in good faith to assist the user in determining whether our products are suitable for his application. No warranty or representation, however is intended or made, nor is protection from any law or patent to be inferred, and all patent rights are reserved. Before using, user shall determine the suitability of the product for his intended use, and user assumes all risk and liability whatsoever in connection therewith. In no event will PTM&W Industries, Inc. be liable for incidental or consequential damages. Buyer's sole and exclusive remedy in such instances shall be limited to replacement of the purchase price.

REPLICAST 612, Page 2

HANDLING and CURING

REPLICAST 612 is very similar to other REPLICAST products that have been on the market for quite some time. However, REPLICAST 612 offers certain advantages over previous products of this type that make it very attractive for use in a variety of applications. It has a longer working time to allow easier preparation and pouring of complicated castings, yet it cures quite rapidly, so it can be demolded in a short time. The exact demold time will depend upon the shop conditions and size of the casting. Generally, most castings can be demolded in 30 to 40 minutes, depending upon size, and can be put into service shortly after that. Very thin casts, and those made in very cold shop environments should be carefully checked for hardness and degree of cure before demolding, to avoid distortion of the casting. REPLICAST 609 is a better choice for thin-section and small castings, as it gels and cures faster in these instances. REPLICAST 612 is a highly filled system, and, as such, both components should be checked for settling before making a casting. REPLICAST 612 usually has less hard-pack settling than other products of this type. However, all filled casting systems have the potential to settle in some manner when stored for long periods, so the REPLICAST resin and hardener should be thoroughly stirred before use to insure original manufactured uniformity.

REPLICAST 612 A/B Test Method Mix Ratio, **By Weight** 100:100 **PTM&W By Volume** 100:100 Color Metallic Grav Visual Mixed Viscosity, @ 77°F, centipoise 2,600 cps **ASTM D2393** Working Time, 4 fl. Oz. Mass, @77°F 10 minutes **ASTM D2471** Peak Exotherm, 20 lb. Mass, Cast 2 1/2 " Thick 130°F **ASTM D2471** Cured Hardness, Shore D **@ Room Temperature** 84 D **ASTM D2240** @ 150° F 80 D Shrinkage, inch/inch, Mold Number 3, 0.0027 inch / inch **ASTM D2566** Volume: 1.23 Gallon, Size: 10" long x 4.5" Deep Specific Gravity, grams, cc 1.71 **ASTM D1475 Pounds per cubic Inch** .0618 Density, **ASTM D792** Pounds per gallon 14.2 Specific Volume, cu. in./lb. 16.19 **ASTM D792** Tensile Strength, psi 4500 psi **ASTM D638** Elongation at Break, % 2.00% Flexural Strength, psi **ASTM D790** 6900 psi **Compressive Strength**, psi 9100 psi ASTM D695

TYPICAL MECHANICAL PROPERTIES

PACKAGING WEIGHTS

	Gallon Kit	Kit Volume	
		Gallons	Cubic Inches
REPLICAST 612 Part A	9 lb.	.62 gal.	144 cu. in.
REPLICAST 612 Part B	9 lb.	.64 gal.	147 cu. in.
Kit	18 lb.	1.26 gallons	291 cubic inches

REPLICAST 612 Bulletin / ZW-38 / 100803-C1



PTM&W Industries, Inc.

10640 S. Painter Avenue Santa Fe Springs, CA 90670-4092 562-946-4511 800-421-1518 FAX: 562-941-4773 Visit Us At: www.ptm-w.com Send Questions To: info@ptm-w.com



Curbell Plastics is a proud supplier of PTM&W materials