

## Technical Data Sheet

### Sustarin<sup>®</sup> C MG - ASTM

[Hostaform<sup>®</sup> MT2U06 / Medical Grade Acetal]

#### Product characteristics

- Good combination of rigidity, stiffness and toughness
- Multi-sterilisable with hot steam, plasma as well as ethylene oxide
- Low moisture absorption

#### Product applications

- Medical engineering
- Pharmaceutical industry

	Test method	Unit	Guideline Value
<b>General properties</b>			
Density	ASTM D792	g / cm <sup>3</sup>	1.41
Water Absorption	ASTM D570	%	0.9
Water Absorption 24 hours	ASTM D570	%	0.2
<b>Mechanical properties</b>			
Hardness	ASTM D2240	Shore D	85
Tensile Strength at yield 73°F	ASTM D638	psi	9500
Tensile Modulus	ASTM D638	psi	400000
Elongation at Break	ASTM D638	%	40
Flexural Strength	ASTM D790	psi	12000
Flexural Modulus	ASTM D790	psi	400000
Rockwell Hardness	ASTM D785	M	88
Rockwell Hardness	ASTM D785	R	120
Izod Impact, Notched	ASTM D256	ft-lb/in	1.2
Coefficient of Friction, Dynamic			0.21
<b>Thermal properties</b>			
Thermal Conductivity		in/hr/ft <sup>2</sup> /°F	1.6
Coefficient of Linear Thermal Expansion	ASTM D696	in/in/°F x10 <sup>-5</sup>	5.5
Melting Point		°F	330
Continuous Service Temperature, Air		°F	180
Deflection Temperature at 1.8Mpa (264psi)	ASTM D648	°F	225
Deflection Temperature at 1.8Mpa (66psi)	ASTM D648	°F	320
Flammability, UL94		1/8 inch	HB
<b>Electrical properties</b>			
Surface resistivity	ASTM D257	Ω/cm	10 <sup>16</sup>
<b>Compliance Properties</b>			
FDA			Yes



### Technical Data Sheet

## Sustarin<sup>®</sup> C MG - ASTM

[Hostaform<sup>®</sup> MT2U06 / Medical Grade Acetal]

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



**CURBELL**  
PLASTICS

1-888-CURBELL

[www.curbellplastics.com](http://www.curbellplastics.com)

Curbell Plastics is a proud supplier of Röchling materials.

