

# TECAFORM® AH FG blue - Stock Shapes

## Chemical Designation

POM-C (Polyacetal (Copolymer))

## Colour

blue

## Density

1.41 g/cm<sup>3</sup>

## Main features

- food grade blue
- low moisture absorption
- easily machinable to tight tolerance
- good mechanical properties
- good wear properties

## Target Industries

- food processing
- food technology
- food engineering
- packaging and paper machinery
- conveyor technology
- engineering for beverage filling systems
- pharmaceutical industry

Mechanical properties	condition	value	test method	comment
Modulus of elasticity (tensile test)	@ 73 °F	250,000 psi	ASTM D 638	(1) Data obtained from public source
Tensile strength at yield	@ 73 °F	8,800 psi	ASTM D 638	(2) Data obtained from public source
Tensile strength at break	@ 73 °F	9,700 psi	ASTM D 638	(3) Data obtained from public source
Elongation at yield	@ 73 °F	9 %	ASTM D 638	(4) Injection molded data
Elongation at break	@ 73 °F	25 %	ASTM D 638	(5) Injection molded data
Flexural strength	@ 73 °F	12,000 psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	400,000 psi	ASTM D 790	
Compression strength	@ 73 °F, 10% strain	11,500 psi	ASTM D 695	3)
Compression strength	@ 73 °F, 1% strain	1,200 psi	ASTM D 695	
Impact strength (Izod)	@ 73 °F	1.1 ft-lbs/in	ASTM D 256	
Rockwell hardness	M Scale	86	ASTM D 785	
Coefficient of friction	Dynamic, 40 psi, 50 fpm	0.21 %	ASTM D 3702	4)
Wear rate	Against Steel, 40 psi, 50 fpm	65*10 <sup>-10</sup> in <sup>3</sup> -min/ft-lbs-hr	ASTM D 3702	5)
Thermal properties	condition	value	test method	comment
Melting temperature		329 °F	-	1)
Deflection temperature	@264 psi	230 °F	ASTM D 648	2)
Deflection temperature	@ 66 psi	316 °F	ASTM D 648	3)
Service temperature	Long Term	195 °F	-	4)
Service temperature	Intermittent	285 °F	-	5)
Thermal expansion (CLTE)		4.7*10 <sup>-5</sup> in/in/°F	ASTM D 696	6)
Electrical properties	condition	value	test method	comment
Volume resistivity		1.0*10 <sup>-14</sup> Ω/square	ASTM D 257	1)
Dielectric strength		500 V/mil	ASTM D 149	2)
Dissipation factor	@ 60HZ, 73°F	0.001	-	3)
Dielectric loss factor	@60 Hz, 70°	0.001	ASTM D 150	4)
Dielectric constant	@ 60HZ, 73°F, 50% RH	3.7	ASTM D 150	5)
Other properties	condition	value	test method	comment
Moisture absorption	@ saturation, 73 °F	0.8 %	ASTM D 570	
Moisture absorption	@ 24 hrs, 73 °F	0.22 %	ASTM D 570	

→ Resin specification:  
ASTM D6778-06 POM211 superseding ASTM D4181-00 POM211  
Shapes specification:  
ASTM D6100-11 S-POM211

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at [www.ensingerplastics.com](http://www.ensingerplastics.com).

Ensinger Inc. Headquarters  
365 Meadowlands Boulevard  
Washington, PA 15301, USA

Phone 800-243-3221 Sales  
Phone 800-869-4029 Technical  
Fax 724-746-9209  
[sales@ensinger-ind.com](mailto:sales@ensinger-ind.com)

Date: 2016/08/04

Version: A0

**CURBELL**  
PLASTICS

1-888-CURBELL

[www.curbellplastics.com](http://www.curbellplastics.com)

Curbell Plastics is a proud supplier of Ensinger materials.