

TECAPEEK CMF white - Stock Shapes (rods, plates, tubes)

Chemical Designation

PEEK (Polyetheretherketone)

Colour

white

Density

1.63 g/cm³

Fillers

ceramic

Main features

- high dimensional stability
- good machinability
- high strength
- high stiffness
- low thermal expansion
- low burring
- good heat deflection temperature
- very good thermal stability

Target Industries

- electrical engineering
- precision engineering
- semiconductor technology
- vacuum technology

Mechanical properties	condition	value	test method	comment
Modulus of elasticity (tensile test)	@ 73 °F	1,227,111 psi	ASTM D 638	1) (1) All properties derived from machined plate test specimens
Tensile strength at yield	@ 73 °F	14,122 psi	ASTM D 638	(2) Data obtained from public source
Tensile strength at break	50 mm/min	15,200 psi	DIN EN ISO 527-2	2) (3) Data obtained from public source
Elongation at yield	50 mm/min	3 %	DIN EN ISO 527-1	3)
Elongation at break	@ 73 °F	4.85 %	ASTM D 638	
Flexural strength	@ 73 °F	23,642 psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	783,585 psi	ASTM D 790	
Compression strength	@ 73 °F @ 10% strain	20,712 psi	ASTM D 695	
Compression strength	@ 73 °F @ 1% strain	1,855 psi	ASTM D 695	
Compression modulus	@ 73 °F	335,369 psi	ASTM D 695	
Impact strength (Izod)	@ 73 °F notched	0.66 ft-lbs/in	ASTM D 256	
Impact strength (Izod)	@ 73 °F unnotched	15.23 ft-lbs/in	ASTM D 256	
Rockwell hardness	M-Scale	102	ASTM D 785	
Thermal properties	condition	value	test method	comment
Melting temperature		643 °F	-	1) (1) ASTM D3418
Service temperature	Long Term	500 °F	-	2) (2) Data obtained from public source
Service temperature	short term	500 °F	-	
Thermal expansion (CLTE)		3.10 *10 ⁻⁵ in/in/°F	ASTM E 831	
Thermal conductivity		2.60 BTU-in/hr-ft ² -°F	ASTM E1530	
Electrical properties	condition	value	test method	comment
surface resistivity		5.2E+15	ASTM D 257	
Volume resistivity		3.5E+15 Ω/square	ASTM D 257	
Dielectric strength	S/T, in oil	168 V/mil	ASTM D 149	
Dissipation factor	1 MHz dry	0.0032	ASTM D 150	
Dielectric constant	1 MHz dry	4.71	ASTM D 150	
Other properties	condition	value	test method	comment
Moisture absorption	@ 24 hrs	0.06 %	-	(1) Data obtained from public source
Flammability (UL94)		V0	-	1)

→ TECAPEEK products are based on Victrex® PEEK polymer.

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.

Ensinger Inc. Headquarters
365 Meadowlands Boulevard
Washington, PA 15301, USA

Phone 800-243-3221 Sales
Phone 800-869-4029 Technical
Fax 724-746-9209
sales@ensinger-ind.com

Date: 2020/09/01

Version: A1

CURBELL
PLASTICS

1-888-CURBELL

www.curbellplastics.com