

## TECAPEEK ® ID blue - Stock Shapes

## **Chemical Designation**

PEEK (Polyetheretherketone)

Colour

blue grey

Density

1.44 g/cm<sup>3</sup>

**Fillers** 

detectable filler

## Main features

- → detectable via metal detector
- → very good chemical resistance
- → hydrolysis and superheated steam resistant
- → good heat deflection temperature
- → high creep resistance
- → inherent flame resistance
- → good machinability

## Target Industries

- → food processing
- → food technology
- → engineering for beverage filling systems
- packaging and paper machinery
- → conveyor technology
- → pharmaceutical industry
- → mechanical engineering

Mechanical properties	condition	value		test method		comment
Modulus of elasticity (tensile test)	(1mm/min)	624,000	psi	DIN EN ISO 527-2		(1) Data obtained from public source (2) Data obtained from public source (3) Data obtained from public source (4) Data obtained from public source
Tensile strength at yield	50 mm/min	14,500	psi	DIN EN ISO 527-2	_	
Tensile strength at break	50 mm/min	16,100	psi	DIN EN ISO 527-2	1)	
Elongation at yield	50 mm/min	4	%	DIN EN ISO 527-1	2)	
Elongation at break	@ 73 °F	4	%	DIN EN ISO 527-2		
Flexural strength	2 mm/min 10N	24,100	psi	DIN EN ISO 178	3)	
Modulus of elasticity (flexural test)		638,000	psi	ASTM D 790		
Compression modulus	5 mm/min 10N	696,000	psi	EN ISO 604	4)	
Impact strength (Charpy)		21.4	ft-lbs/in	DIN EN ISO 179-1		
Thermal properties	condition	value	_	test method	-	comment
Glass transition temperature		289	°F	DIN 53765		
Melting temperature		649	°F	DIN 53765	_	<b></b>
Service temperature	Long Term	500	°F	-		
Service temperature	Intermittent	572	°F	-		
Electrical properties	condition	value		test method	_	comment
Specific surface resistance		1.0*10 <sup>14</sup>	Ω/square	-	1)	(1) Data obtained from public
Specific volume resistance		1.0*10 <sup>14</sup>	Ω*cm	-	2)	<ul> <li>source</li> <li>(2) Data obtained from public source</li> </ul>
Other properties	condition	value		test method		comment
Moisture absorption	@ 24 hrs. 73°F	0.02	%	ASTM D 570	1)	(1) Data obtained from public source (2) Data obtained from public source
Moisture absorption		0.03	%	ASTM D 570	2)	
Flammability (UL94)		V0		-		

<sup>→</sup> TECAPEEK products are based on Victrex® PEEK polymer.

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.

Ensinger Inc. Headquarters 365 Meadow lands Boulevard Washington, PA 15301, USA Phone 800-243-3221 Sales Phone 800-869-4029 Technical Fax 724-746-9209 sales@ensinger-ind.com Date: 2015/11/05



1-888-CURBELL www.curbellplastics.com

Version: A0

Curbell Plastics is a proud supplier of Ensinger materials.