

TECAPEEK SM natural

Chemical designation

Mechanical properties

PEEK (polyetheretherketone)

Colour

Beige opaque

Density

1.31 g/cm³

Main features

parameter

- electrically insulating
- → high thermal and mechanical capacity
- → hydrolysis and superheated steam resistant
- → good chemical resistance
- → flame retardant according to UL94 V-0
- good machinability
- good slide and wear properties
- resistant to many solvents

Target Industries

- oil and gas industry
- chemical technology
- mechanical engineering
- electrical engineering
- → aircraft and aerospace technology

comment

- → food engineering
- automotive industry
- → semiconductor technology
- → vacuum technology
- → textile industry

Melting temperature	chart tarm	341	°C		2)	Individual testing regarding
Glass transition temperature		150	გ	DIN 53765	1)	(1) Found in public sources. (2) Found in public sources.
Thermal properties	parameter	value	unit	norm		comment
Shore D hardness		88		BS EN ISO 868		00000
Modulus of elasticity (flexural test)		3670	MPa			инин
Flexural strength		164	MPa			
Elongation at break		19	%	BS EN ISO 527-2		
Elongation at yield		3.6	%	BS EN ISO 527-2		
Tensile strength at yield		102	MPa	BS EN ISO 527-2		
Tensile strength		102	MPa	BS EN ISO 527-2		
Modulus of elasticity (tensile test)		3520	MPa	BS EN ISO 527-2		

value

unit

norm

BS EN ISO 527-2

Glass transition temperature		150	v.	DIN 53765	1)	(1) Found in public sources.
 Melting temperature		341	$\mathcal C$			(2) Found in public sources. Individual testing regarding
 Service temperature	short term	300	$\mathcal C$		2)	application conditions is
Service temperature	long term	260	$\mathcal C$			mandatory.



Date: 2015/01/19



Curbell Plastics is a proud supplier of Ensinger materials.

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes.