

TECAPEI™ natural (Sabic Ultem® 1000 series) - Stock Shapes (rods, plates, tubes)

Chemical Designation

PEI (Polyetherimide)

Colour

amber transparent transparent

Density

1.27 g/cm³

Main features

- high dielectric strength
- inherent flame retardant
- low smoke emissions
- easily machinable to tight tolerance
- high thermal and mechanical capacity
- flame retardant according to UL94 V-0

Target Industries

- aircraft and aerospace technology
- automotive industry
- electronics
- medical technology
- semiconductor technology
- food engineering
- food processing

| Mechanical properties | condition | value | | test method | comment |
|---------------------------------------|----------------------|------------------------|-------------------------------|-------------|--|
| Modulus of elasticity (tensile test) | @ 73 °F | 430,000 | psi | ASTM D 638 | |
| Tensile strength at break | @ 73 °F | 17,500 | psi | ASTM D 638 | |
| Elongation at yield | @ 73 °F | 7 | % | ASTM D 638 | |
| Elongation at break | @ 73 °F | 40 | % | ASTM D 638 | |
| Flexural strength | @ 73 °F | 23,000 | psi | ASTM D 790 | |
| Modulus of elasticity (flexural test) | @ 73 °F | 480,000 | psi | ASTM D 790 | |
| Compression strength | @ 10% strain | 21,000 | psi | ASTM D 695 | |
| Compression strength | @ 1 % strain | 3,500 | psi | ASTM D 695 | |
| Compression modulus | | 480,000 | psi | ASTM D 695 | |
| Notched impact strength (Izod) | @ 73 °F | 0.60 | ft-lbs/in | ASTM D 256 | |
| Rockwell hardness | R Scale | 126 | | ASTM D 785 | |
| Rockwell hardness | M Scale | 110 | | ASTM D 785 | |
| Thermal properties | condition | value | | test method | comment |
| Vicat softening point | | 426 | °F | ASTM D 1525 | 1) (1) Injection molded data |
| Deflection temperature | @264 psi | 394 | °F | ASTM D 648 | 2) (2) Injection molded data |
| Deflection temperature | @ 66 psi | 410 | °F | ASTM D 648 | 3) (3) Injection molded data |
| Service temperature | Long Term | 338 | °F | - | 4) (4) Data obtained from public source |
| Service temperature | short term | 392 | °F | - | 5) (5) Data obtained from public source |
| Thermal expansion (CLTE) | | 3.1*10 ⁻⁵ | in/in/°F | ASTM E 831 | 6) (6) Injection molded data |
| Thermal conductivity | | 1.5 | BTU-in/hr-ft ² -°F | ASTM D 2214 | 7) (7) Injection molded data |
| Electrical properties | condition | value | | test method | comment |
| Volume resistivity | 1/16 | 1.0 x 10 ¹⁷ | Ω*cm | ASTM D 257 | 1) (1) injection molded data |
| Dielectric strength | In Oil | 709 | V/mil | ASTM D 149 | 2) (2) injection molded data |
| Dielectric strength | In Air | 830 | V/mil | ASTM D 149 | 3) (3) injection molded data |
| Dissipation factor | 1 kHz, 50% RH, 73 °F | 0.0013 | | ASTM D 150 | 4) (4) injection molded data |
| Dielectric constant | 1 kHz, 50% RH | 3.15 | | ASTM D 150 | 5) (5) Injection molded data |
| Other properties | condition | value | | test method | comment |
| Moisture absorption | @ saturation, 73 °F | 1.25 | % | ASTM D 570 | 1) (1) Injection molded data |
| Moisture absorption | @ 24 hrs, 73 °F | .25 | % | ASTM D 570 | 2) (2) injection molded data |
| Flammability | 3 mm | pass | | FAR 25.853 | 3) (3) 3.0 mm specimen |
| Flammability (UL94) | | V0 | | - | 4) (4) Injection molded data (0.75 mm thickness) |

→ Resin specification:
ASTM D 5205-10 PEI0113
Shapes specification:
ASTM D7293-06 S-PEI0111

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.