

DuPont™ Vespel® SCP-50094

Polyimide Isostatic Shapes

Typical ISO Properties

DuPont™ Vespel® SCP-50094 is a proprietary polymer. It is designed for demanding applications that require high temperature and wear resistance.

The typical values presented below are preliminary results and are subject to revision.

Mechanical Properties	Temperature	Pressure	Test Method	Units	Typical Values
Tensile Strength	23 °C (73 °F) 260 °C (500 °F)	—	ASTM D-638 D-1708 Specimen	MPa (kpsi)	124 (18.0) 55 (8.0)
Tensile Elongation	23 °C (73 °F) 260 °C (500 °F)	—	ASTM D-638 D-1708 Specimen	%	4.3 13
Young's Modulus	23 °C (73 °F) 260 °C (500 °F)	—	ASTM D-638 D-1708 Specimen	MPa (kpsi)	4,140 (600) 2,350 (340)
Flexural Strength	23 °C (73 °F) 260 °C (500 °F)	—	ASTM D-790	MPa (kpsi)	200 (29) 96 (14)
Flexural Modulus	23 °C (73 °F) 260 °C (500 °F)	—	ASTM D-790	MPa (kpsi)	6,370 (923) 3,540 (514)
Compressive Strength	23 °C (73 °F) 260 °C (500 °F)	—	ASTM D-695	MPa (kpsi)	385 (56) 450 (65)
Compressive Strain, Ultimate	23 °C (73 °F) 260 °C (500 °F)	—	ASTM D-695	MPa (kpsi)	41 63
Compressive Stress at 10% Strain	23 °C (73 °F) 260 °C (500 °F)	—	ASTM D-695	MPa (kpsi)	220 (31.9) 81 (11.7)
Deformation Under Load after 24 hours	23 °C (73 °F)	14 MPa (2.5 kpsi)	ASTM D-621	% deformation	0.05
Compressive Creep, 10 hr 100 hr 1000 hr	23 °C (73 °F)	10 MPa (1.5 kpsi)	ASTM D-2990	%	0.02 0.02 0.05
Compressive Creep, 10 hr 100 hr 1000 hr	23 °C (73 °F)	14 MPa (2.5 kpsi)	ASTM D-2990	%	0.03 0.05 0.07
Rockwell "E" hardness	—	—	ASTM D-785	—	91
Poisson's Ratio	23 °C (73 °F) 260 °C (500 °F)	—	ASTM D-638	—	0.34 0.34

continued



The miracles of science™

Thermal Properties	Temperature	Pressure	Test Method	Units	Typical Values
Coefficient of Thermal Expansion Parallel Perpendicular	50–150 °C (122–302 °F)	—	ASTM E-831	m/m·°C or m/m·K (in/in·°F)	42.7 x 10 ⁻⁶ (23.7 x 10 ⁻⁶)
Thermal Conductivity	50 °C (122 °F) 100 °C (212 °F) 300 °C (572 °F)	—	ASTM F-433	W/m·K (Btu/hr·in·°F)	0.59 (0.03) 0.66 (0.03) 0.58 (0.03)
Specific Heat	60 °C (140 °F)	—	ASTM E-1269	J/kg·°C (Btu/lb·°F)	9.2 x 10 ⁵ (0.22)
Wear Properties	Velocity	Pressure	Test Method	Units	Typical Values
Coefficient of Friction, Unlubricated, Air 0.88 (25K) PV 3.50 (100K) PV 10.50 (300K) PV	0.7 m/s (134 fpm) 2.0 m/s (400 fpm) 3.0 m/s (585 fpm)	1.3 MPa (187 psi) 1.7 MPa (250 psi) 3.5 MPa (500 psi)	Falex	—	0.25 0.07 0.11
Wear Factor, Unlubricated, Air 0.88 (25K) PV 3.50 (100K) PV 10.50 (300K) PV	0.7 m/s (134 fpm) 2.0 m/s (400 fpm) 3.0 m/s (585 fpm)	1.3 MPa (187 psi) 1.7 MPa (250 psi) 3.5 MPa (500 psi)	Falex	mm-sec/MPa-m-hr (in ³ -min/ft-lb-hr)	1.7 x 10 ⁻³ (24 x 10 ⁻¹⁰) 0.8 x 10 ⁻³ (11 x 10 ⁻¹⁰) 1.2 x 10 ⁻³ (17 x 10 ⁻¹⁰)
Other Properties	Temperature	Time	Test Method	Units	Typical Values
Specific Gravity	23 °C (73 °F)	—	ASTM D-792	—	1.50
Water Absorption	23 °C (73 °F)	24 hr	ASTM D-570	% weight change	0.06

Visit us at kalrez.dupont.com or vespel.dupont.com

Contact DuPont at the following regional locations:

North America
800-222-8377

Latin America
+0800 17 17 15

Europe, Middle East, Africa
+41 22 717 51 11

Greater China
+86-400-8851-888

ASEAN
+65-6586-3688

Japan
+81-3-5521-8484

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont customer service representative and read Medical Caution Statement H-50103-3.

Copyright © 2011 DuPont. The DuPont Oval Logo, DuPont™, The miracles of science™, Kalrez® and Vespel® are trademarks or registered trademarks of E. I. du Pont de Nemours and Company or its affiliates. All rights reserved.

(04/09) Reference No. VPE-A10993-00-A0911 Previous Reference No. K-21997



The miracles of science™

AUTHORIZED DISTRIBUTOR

DuPont™ Vespel®
PARTS & SHAPES



Supplying Authentic Vespel® Shapes

Curbell Plastics is a proud supplier of DuPont™ Vespel® Polyimide Shapes.

1.888.CURBELL • www.curbellplastics.com

CURBELL
PLASTICS