



DuPont™ Vespel® SF

POLYIMIDE FOAM PARTS

Typical Polyimide Foam Properties

DuPont™ Vespel® SF parts and shapes are foam products used in applications requiring thermal insulation at high temperatures. Products are available in various densities to provide different mechanical properties.

Some data presented below are based on limited production runs and are subject to revision as new knowledge and experience become available.

Physical Property	Test Method	Unit	SF-0920 (Low Density)	SF-0930 (Med. Density)	SF-0940 (High Density)
Density Range	ASTM D3574 Test E	g/cc lb/ft ³	0.15 ± 0.05 9.36 ± 3.0	0.3 ± 0.1 18.7 ± 6.0	0.5 ± 0.1 31.2 ± 6.0
Max Standard Thk		mm in	36.0 1.42	12.0 0.47	6.0 0.24
Standard Sheet Size		mm in	575 x 575 ~23 x 23	525 x 525 ~21 x 21	450 x 450 ~18 x 18
Mechanical Property					
Ultimate Tensile Strength	ASTM D3574 Test E	kPa psi	425 61.6	4,400 640	26,000 3,770
Tensile Modulus	ASTM D3574 Test E	kPa psi	—	106,700 15,480	521,200 75,600
Elongation at Break	ASTM D3574 Test E	%	—	7.94	9.08
Compression Force Test at 20%	ASTM D3574 Test C	kPa psi	120 17.4	1,760 255	32,400 4,700
Compression Force Test at 40%	ASTM D3574 Test C	kPa psi	200 29	3,800 550	52,700 7,640
Compression Modulus	ASTM D1621	kPa psi	—	1,640 238	320,600 46,500
Compressive Strength at 10%	ASTM D1621	kPa psi	—	2,000 290	25,400 3,680
Compressive Strength at 20%	ASTM D1621	kPa psi	—	3,400 490	41,000 6,000
Relative Permittivity (Dielectric Constant)	ASTM D1673	—	1.11	1.39	1.9
Dissipation (Capacitance) Factor	ASTM D1673	pf	2.52	3.04	4.21



The miracles of science™

DuPont™ Vespel® SF-0900 Typical Direct-Formed Properties *(continued)*

Thermal	Test Method	Unit	SF-0920 (Low Density)	SF-0930 (Med. Density)	SF-0940 (Low Density)
Continuous Use Temperature	—	°C °F	300 572	300 572	300 572
Thermal Conductivity 25 °C (77 °F)	ASTM C518	W/(m-K)	0.033–0.036	0.0467	0.0657
CLTE (60–130 °F)	ASTM E228	10 ⁻⁶ in/in/°F	0.28	—	—
CLTE (130–200 °F)	ASTM E228	10 ⁻⁶ in/in/°F	0.13	—	—

CURBELL
PLASTICS

1-888-CURBELL

www.curbellplastics.com

Curbell Plastics is a proud supplier of DuPont™ materials.

DUPONT
Authorized Distributor

Visit us at kalrez.dupont.com or vespel.dupont.com

Contact DuPont at the following regional locations:

North America
800-222-8377

Latin America
+0800 17 17 15

Europe, Middle East, Africa
+41 22 717 51 11

Greater China
+86-400-8851-888

ASEAN
+65-6586-3688

Japan
+81-3-5521-8484

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont customer service representative and read Medical Caution Statement H-50103-3.

Copyright © 2010 DuPont. The DuPont Oval Logo, DuPont™, The miracles of science™, Kalrez®, and Vespel® are trademarks or registered trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

(10/10) Reference No. VPE-A10887-00-A1010



The miracles of science™