

KYDEX® 510

Weatherable and decorative sheet

INTRODUCTION

KYDEX® 510 is a weatherable sheet with superior performance for thermoforming and a decorative sheet for lamination.

GENERAL INFORMATION

KYDEX® 510 is available in many distinctive colors and textures. An acrylic cap protects the surface, providing excellent weatherability for outdoor use. This product is now available with decorative film (black/white granite). While excellent in thermoforming, KYDEX® 510 is also being used as damage resistant surface material.

SUGGESTED APPLICATIONS

- Kiosk Housings
- Medical Products
- Equipment Housings
- Miscellaneous Applications

FEATURES

- Offers same properties of KYDEX® sheet, but in a weatherable formula
- Highly impact resistant as measured by the Notched Izod Impact Resistance test
- Fire retardant (self-extinguishing) with UL Std 94 V-0 and 5V ratings
- Low moisture absorption, resistance to chipping and cracking, great fabrication and machining properties and flexibility
- Excellent forming properties, uniform wall thickness and crisp detail
- Can be drilled, punched and cut using standard woodworking or metal working tools
- Exhibits a Dielectric Constant of 2.76 @ 100 Hz, 2.53 @ 800 MHz, 2.51 @ 1.9 GHz and 2.80 @ 40 GHz

ENVIRONMENTAL & SAFETY CONSIDERATIONS

SEKISUI KYDEX, LLC is committed to ensuring that its products can be manufactured, transported, stored, used, disposed and recycled with an appropriate regard for safety, health and environmental protection. We support the safe handling of our products. Please contact our Technical Service department at 800.682.8758 for resources or visit our website: <http://www.kydex.com>. For Material Safety Data Sheets, please call 800.325.3133.



Customer Collaboration

6685 Low St, Bloomsburg, PA 17815 USA
Phone: 800.325.3133, +1.570.389.5810
Email: info@kydex.com

appLab™

Phone: 800.682.8758
Email: applab@kydex.com

kydex.com

KYDEX® 510

Weatherable and decorative sheet

PROPERTY	TEST METHOD	TYPICAL VALUE ¹	
PHYSICAL			
Specific Gravity	ASTM D792	1.35	
Rockwell Hardness, R-scale	ASTM D785	94	
MECHANICAL			
Tensile Strength	ASTM D638	42 MPa	6,100 psi
Flexural Strength	ASTM D790	66 MPa	9,600 psi
Flexural Modulus	ASTM D790	2,480 MPa	360,000 psi
Izod Impact, notched	ASTM D256	801 J/m	15 ft-lb _f /in
Coefficient of Linear Thermal Expansion	ASTM D696	6.9x10 ⁻⁵ / °C	3.83 x 10 ⁻⁵ / °F
THERMAL			
Heat Deflection Temperature (HDT) @ 264 psi (1.8 MPa) annealed	ASTM D648	75.6°C	168°F
ELECTRICAL			
Dielectric Strength, oil	ASTM D149	19.7 kV/mm	500 V/mil
FLAMMABILITY			
Underwriters Laboratories, Inc. [®] Component Recognition	UL Standard 94 ²	V-0, 5V ³	
¹ Values based upon 3.18mm (0.125") sheet unless otherwise specified. ² Underwriters Laboratories, Inc. [®] , File Number E115252 ³ All thicknesses 0.71mm (0.028") and above Not intended for specification purposes.			



Customer Collaboration
6685 Low St, Bloomsburg, PA 17815 USA
Phone: 800.325.3133, +1.570.389.5810
Email: info@kydex.com

applab™
Phone: 800.682.8758
Email: applab@kydex.com

kydex.com

CURBELL
PLASTICS

1-888-CURBELL

www.curbellplastics.com

Curbell Plastics is a proud supplier of SEKISUI materials.

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. The products discussed are sold without warranty of merchantability or fitness for a particular use, either expressed or implied, except as provided in our standard terms and conditions of sale. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our product. Product not intended for use as a heat resistant surface. Texture, product grade and other conditions may cause variations in appearance.